

# (12) UK Patent Application (19) GB (11) 2 301 106 (13) A

(43) Date of A Publication 27.11.1996

(21) Application No 9607380.4

(22) Date of Filing 09.04.1996

(30) Priority Data

(31) 106995

(32) 11.04.1995

(33) CH

(71) Applicant(s)

Ciba-Geigy AG

(Incorporated in Switzerland)

Klybeckstrasse 141, CH-4002 Basle, Switzerland

(72) Inventor(s)

Francois Gugumus

(74) Agent and/or Address for Service

T Sharman

Ciba-Geigy PLC, Patent Department,  
Central Research, Hulley Road, MACCLESFIELD,  
Cheshire, SK10 2NX, United Kingdom

(51) INT CL<sup>6</sup>

C08K 5/3435 , C07D 211/46 401/14 519/00 , C08K 5/3492 , // C08L 23/06 53/00 101/00 ( C08K 5/3435 5:353 5:54 ) ( C08K 5/3492 5:353 5:54 ) ( C08L 101/00 79:00 ) ( C07D 401/14 207:40 211:58 211:94 251:70 ) ( C07D 519/00 493:10 498:10 )


(52) UK CL (Edition O )

C3K KCZ K201 K210 K211 K230 K274 K277 K279 K283 K284 K290 K291 K292 K294 K296 K297 K298 K299 C2C CAA CBG CLH CNE CTP CTR C1182 C1342 C1371 C1532 C1562 C1652 C1691 C211 C215 C22Y C220 C221 C225 C226 C246 C247 C25Y C250 C251 C252 C253 C255 C28X C30Y C32Y C322 C323 C351 C352 C36Y C360 C362 C364 C366 C368 C37X C38Y C386 C388 C45Y C456 C50Y C500 C610 C619 C640 C643 C644 C645 C648 C65X C652 C658 C660 C662 C67X C670 C672 C680 C682 C699 C761 C762 C763 C774 C775 C80Y C806 C3W W100 W111 W112 W114 W121 W123 W205 W208 W213 W215 W216 W217 W218 W218A W219 W221 W224 W225 W226 W228 W303 W304 W305 W308 W314 W315 W316 W317 W321 W323 W327 W328 U1S S1349


(56) and (58) continued overleaf

(54) Synergistic stabilizer mixture for organic materials; organic compounds

(57) Stabilizer mixture comprising, for example, a compound of the formula and, for example, a compound of the formula



and, for example, a compound of the formula



Some of the compounds of the mixture are also claimed.

GB 2 301 106 A

(56) Documents Cited

GB 2267499 A WO 94/22946 A2 WO 92/12201 A1  
US 4957953 A

(58) Field of Search

UK CL (Edition O ) C3K KCB KCZ  
INT CL<sup>6</sup> C08K 5/00 5/3435 5/3492 5/54

Synergistic stabilizer mixture


The present invention relates to a stabilizer system comprising two specific polyalkylpiperidine derivatives, some of which are novel, to the use of this stabilizer system for stabilizing organic material, and to the organic material protected against thermal, oxidative or light-induced degradation by means of the stabilizer system mentioned.

Polyalkylpiperidine derivatives are described for example in WO-A-94/12 544, US-A-4 110 334 and US-A-5 204 473.

US-A-4 692 486, US-A-4 863 981, US-A-4 957 953, WO-A-92/12 201, WO-A-94/22 946, EP-A-449 685, EP-A-632 092, GB-A-2 267 499 and Research Disclosure 34 549 (January 1993) describe some stabilizer mixtures which comprise two polyalkylpiperidine derivatives.

The present invention relates to a stabilizer mixture comprising a component I-a), I-b), I-c), I-d), I-e), I-f), I-g), I-h), I-i), I-j), I-k) or I-l) and a component II-a), II-b), II-c), II-d), II-e), II-f), II-g), II-h), II-i), II-j), II-k), II-l) or II-m), where

component I-a) is at least one compound of the formula I-1



in which

R<sub>1</sub> is hydrogen, C<sub>1</sub>-C<sub>18</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>cycloalkyl or C<sub>1</sub>-C<sub>4</sub>alkyl-substituted C<sub>5</sub>-C<sub>12</sub>cycloalkyl,

n<sub>1</sub> is 1, 2 or 4,

if n<sub>1</sub> is 1, R<sub>2</sub> is C<sub>1</sub>-C<sub>25</sub>alkyl,

if n<sub>1</sub> is 2, R<sub>2</sub> is C<sub>1</sub>-C<sub>14</sub>alkylene and

if n<sub>1</sub> is 4, R<sub>2</sub> is C<sub>4</sub>-C<sub>10</sub>alkanetetrayl,


with the provisos that,

(1) in a stabilizer mixture comprising component I-a) and component II-b) or II-m), if

$n_1=2$ ,  $R_1$  is other than  $C_1-C_{18}$ alkyl and

(2) in a stabilizer mixture comprising component I-a) and component II-d), if  $n_1=2$  and  $R_1=C_1-C_{18}$ alkyl, the group  $-N(A_{14})A_{15}$  is a 5- to 10-membered heterocyclic ring;

component I-b) is at least one compound of the formula II-1




in which

$R_3$  and  $R_7$  independently of one another are hydrogen or  $C_1-C_{12}$ alkyl.

$R_4$ ,  $R_5$  and  $R_6$  independently of one another are  $C_2-C_{10}$ alkylene and

$X_1$ ,  $X_2$ ,  $X_3$ ,  $X_4$ ,  $X_5$ ,  $X_6$ ,  $X_7$  and  $X_8$  independently of one another are a group of the formula III-1




in which

$R_8$  is hydrogen,  $C_1-C_{12}$ alkyl,  $C_5-C_{12}$ cycloalkyl,  $C_1-C_4$ alkyl-substituted  $C_5-C_{12}$ cycloalkyl, phenyl, -OH- and/or  $C_1-C_{10}$ alkyl-substituted phenyl,  $C_7-C_9$ phenylalkyl,  $C_7-C_9$ phenylalkyl which is substituted on the phenyl radical by -OH and/or  $C_1-C_{10}$ alkyl, or is a group of the formula IV-1



and  $R_9$  and  $R_{10}$  independently of one another are as defined for  $R_1$ ;

component I-c) is at least one compound of the formula V-1




(V-1)

in which

$\text{X}_9$ ,  $\text{X}_{10}$  and  $\text{X}_{11}$  independently of one another are a group of the formula III-1;

component I-d) is at least one compound of the formula VI-1




(VI-1)

in which

$\text{R}_{11}$ ,  $\text{R}_{13}$ ,  $\text{R}_{14}$  and  $\text{R}_{15}$  independently of one another are hydrogen,  $\text{C}_1$ - $\text{C}_{12}$ alkyl,  $\text{C}_5$ - $\text{C}_{12}$ cycloalkyl,  $\text{C}_1$ - $\text{C}_4$ alkyl-substituted  $\text{C}_5$ - $\text{C}_{12}$ cycloalkyl, phenyl, -OH- and/or  $\text{C}_1$ - $\text{C}_{10}$ alkyl-substituted phenyl,  $\text{C}_7$ - $\text{C}_9$ phenylalkyl,  $\text{C}_7$ - $\text{C}_9$ phenylalkyl which is substituted on the phenyl radical by -OH and/or  $\text{C}_1$ - $\text{C}_{10}$ alkyl, or are a group of the formula IV-1,  $\text{R}_{12}$  is  $\text{C}_2$ - $\text{C}_{18}$ alkylene,  $\text{C}_5$ - $\text{C}_7$ cycloalkylene or  $\text{C}_1$ - $\text{C}_4$ alkylenedi( $\text{C}_5$ - $\text{C}_7$ cycloalkylene), or the radicals  $\text{R}_{11}$ ,  $\text{R}_{12}$  and  $\text{R}_{13}$ , together with the nitrogen atoms to which they are attached, form a 5- to 10-membered heterocyclic ring, or  $\text{R}_{14}$  and  $\text{R}_{15}$ , together with the nitrogen atom to which they are attached, form a 5- to 10-membered heterocyclic ring,  $n_2$  is a number from 2 to 50 and at least one of the radicals  $\text{R}_{11}$ ,  $\text{R}_{13}$ ,  $\text{R}_{14}$  and  $\text{R}_{15}$  is a group of the formula IV-1;

component I-e) is at least one compound of the formula VII-1



(VII-1)

in which

$R_{16}$  is  $C_1$ - $C_{10}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl,  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl, phenyl or  $C_1$ - $C_{10}$ alkyl-substituted phenyl,


$R_{17}$  is  $C_3$ - $C_{10}$ alkylene,

$R_{18}$  is as defined for  $R_1$  and


$n_3$  is a number from 1 to 50;

component I-f) is a product obtainable by


a) reacting a product, obtained by reaction of a polyamine of the formula VIII-1-a with cyanuric chloride, with a compound of the formula VIII-1-b



(VIII-1-a)



(VIII-1-b)




in which

$n_4'$ ,  $n_4''$  and  $n_4'''$  independently of one another are a number from 2 to 12 and

$R_{19}$  is hydrogen,  $C_1$ - $C_{12}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl or  $C_7$ - $C_9$ phenylalkyl, and


b) further reacting the 2,2,6,6-tetramethylpiperid-4-yl groups present in the molecule to give groups of the formula VIII-1-c



(VIII-1-c)

in which  $R_{20}$  is as defined for  $R_1$ ;

component I-g) is at least one compound of the formula IX-1



(IX-1)

in which

$R_{21}$  and  $R_{26}$  independently of one another are a direct bond or a group

$-N(Y_1)-CO-Y_2-CO-N(Y_3)-$ ,

$Y_1$  and  $Y_3$  independently of one another are hydrogen,  $C_1-C_8$ alkyl,  $C_5-C_{12}$ cycloalkyl, phenyl,  $C_7-C_9$ phenylalkyl or a group of the formula IV-1,

$Y_2$  is a direct bond or  $C_1-C_4$ alkylene,

$R_{22}$  is as defined for  $R_1$ ,


$R_{23}$ ,  $R_{24}$ ,  $R_{27}$  and  $R_{28}$  independently of one another are hydrogen,  $C_1-C_{30}$ alkyl,

$C_5-C_{12}$ cycloalkyl or phenyl,

$R_{25}$  is hydrogen,  $C_1-C_{30}$ alkyl,  $C_5-C_{12}$ cycloalkyl, phenyl,  $C_7-C_9$ phenylalkyl or a group of the formula IV-1 and

$n_5$  is a number from 1 to 50;

component I-h) is at least one compound of the formula X-1




(X-1)

in which

$R_{29}$  is  $C_1$ - $C_{24}$  alkyl and

$R_{30}$  is as defined for  $R_1$ ;

component I-i) is at least one compound of the formula XI-1



(XI-1)


in which

$R_{31}$  is as defined for  $R_1$  and

$n_6$  is a number from 2 to 50;

component I-j) is at least one compound of the formula XII-1






$R_{35}$  is as defined for  $R_1$ ;

$$\left[ \text{C}(=\text{O})-\text{R}_{36}-\text{CH}(\text{R}_{37})-\text{C}(=\text{O})-\text{O}-\text{R}_{39}-\text{O} \begin{array}{c} \diagup \diagdown \\ \diagdown \diagup \end{array} \text{O} \begin{array}{c} \diagup \diagdown \\ \diagdown \diagup \end{array} \text{O}-\text{R}_{40}-\text{O}- \right]_n$$

(XII-1)

$n_7$  is a number from 1 to 50;


component I-1) is at least one compound of the formula XIV-1



(XIV-1)


in which

$X_{12}$ ,  $X_{13}$  and  $X_{14}$  independently of one another are a group of the formula XV-1



in which A is a group of the formula III-1;

component II-a) is at least one compound of the formula I-2



(I-2)

in which

$A_1$  is hydrogen,  $C_1$ - $C_8$ alkyl,  $O^-$ ,  $-\text{CH}_2\text{CN}$ ,  $C_3$ - $C_6$ alkenyl,  $C_7$ - $C_9$ phenylalkyl or  $C_7$ - $C_9$ phenylalkyl which is substituted on the phenyl radical by  $C_1$ - $C_4$ alkyl,


$b_1$  is 1, 2 or 4,

if  $b_1$  is 1,  $A_2$  is  $C_1$ - $C_{25}$ alkyl,

if  $b_1$  is 2,  $A_2$  is  $C_1$ - $C_{14}$ alkylene and

if  $b_1$  is 4,  $A_2$  is  $C_4$ - $C_{10}$ alkanetetrayl;

component II-b) is at least one compound of the formula II-2




(II-2)

in which

$A_3$  and  $A_7$  independently of one another are hydrogen or  $C_1$ - $C_{12}$ alkyl,

$A_4$ ,  $A_5$  and  $A_6$  independently of one another are  $C_2$ - $C_{10}$ alkylene and

T<sub>1</sub>, T<sub>2</sub>, T<sub>3</sub>, T<sub>4</sub>, T<sub>5</sub>, T<sub>6</sub>, T<sub>7</sub> and T<sub>8</sub> independently of one another are a group of the formula III-2



in which A<sub>8</sub> is hydrogen, C<sub>1</sub>-C<sub>12</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>cycloalkyl, C<sub>1</sub>-C<sub>4</sub>alkyl-substituted C<sub>5</sub>-C<sub>12</sub>cycloalkyl, phenyl, -OH- and/or C<sub>1</sub>-C<sub>10</sub>alkyl-substituted phenyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl which is substituted on the phenyl radical by -OH and/or C<sub>1</sub>-C<sub>10</sub>alkyl, or is a group of the formula IV-2



and A<sub>9</sub> and A<sub>10</sub> independently of one another are as defined for A<sub>1</sub>;


component II-c) is at least one compound of the formula V-2



in which

T<sub>9</sub>, T<sub>10</sub> and T<sub>11</sub> independently of one another are a group of the formula III-2;

component II-d) is at least one compound of the formula VI-2



in which

A<sub>11</sub>, A<sub>13</sub>, A<sub>14</sub> and A<sub>15</sub> independently of one another are hydrogen, C<sub>1</sub>-C<sub>12</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>cycloalkyl, C<sub>1</sub>-C<sub>4</sub>alkyl-substituted C<sub>5</sub>-C<sub>12</sub>cycloalkyl, phenyl, -OH- and/or C<sub>1</sub>-C<sub>10</sub>alkyl-substituted phenyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl which is substituted


on the phenyl radical by -OH and/or C<sub>1</sub>-C<sub>10</sub>alkyl, or are a group of the formula IV-2, A<sub>12</sub> is C<sub>2</sub>-C<sub>18</sub>alkylene, C<sub>5</sub>-C<sub>7</sub>cycloalkylene or C<sub>1</sub>-C<sub>4</sub>alkylenedi(C<sub>5</sub>-C<sub>7</sub>cycloalkylene), or the radicals A<sub>11</sub>, A<sub>12</sub> and A<sub>13</sub>, together with the nitrogen atoms to which they are attached, form a 5- to 10-membered heterocyclic ring, or

A<sub>14</sub> and A<sub>15</sub>, together with the nitrogen atom to which they are attached, form a 5- to 10-membered heterocyclic ring,

b<sub>2</sub> is a number from 2 to 50 and

at least one of the radicals A<sub>11</sub>, A<sub>13</sub>, A<sub>14</sub> and A<sub>15</sub> is a group of the formula IV-2;

component II-e) is at least one compound of the formula VII-2



in which


A<sub>16</sub> is C<sub>1</sub>-C<sub>10</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>cycloalkyl, C<sub>1</sub>-C<sub>4</sub>alkyl-substituted C<sub>5</sub>-C<sub>12</sub>cycloalkyl, phenyl or C<sub>1</sub>-C<sub>10</sub>alkyl-substituted phenyl,


A<sub>17</sub> is C<sub>3</sub>-C<sub>10</sub>alkylene,

A<sub>18</sub> is as defined for A<sub>1</sub> and

b<sub>3</sub> is a number from 1 to 50;

component II-f) is a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula VIII-2-a with cyanuric chloride, with a compound of the formula VIII-2-b





(VIII-2-b)


in which

$b_4'$ ,  $b_4''$  and  $b_4'''$  independently of one another are a number from 2 to 12,

$A_{19}$  is hydrogen,  $C_1$ - $C_{12}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl or  $C_7$ - $C_9$ phenylalkyl and

$A_{20}$  is as defined for  $A_1$ ;

component II-g) is at least one compound of the formula IX-2



(IX-2)

in which

$A_{21}$  and  $A_{26}$  independently of one another are a direct bond or a group

$-N(E_1)-CO-E_2-CO-N(E_3)-$ ,

$E_1$  and  $E_3$  independently of one another are hydrogen,  $C_1$ - $C_8$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl,  $C_7$ - $C_9$ phenylalkyl or a group of the formula IV-2,

$E_2$  is a direct bond or  $C_1$ - $C_4$ alkylene,

$A_{22}$  is as defined for  $A_1$ ,


$A_{23}$ ,  $A_{24}$ ,  $A_{27}$  and  $A_{28}$  independently of one another are hydrogen,  $C_1$ - $C_{30}$ alkyl,

$C_5$ - $C_{12}$ cycloalkyl or phenyl,

$A_{25}$  is hydrogen,  $C_1$ - $C_{30}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl,  $C_7$ - $C_9$ phenylalkyl or a group of


the formula IV-2 and  
 $b_5$  is a number from 1 to 50;

component II-h) is at least one compound of the formula X-2




in which  
 $A_{29}$  is  $C_1$ - $C_{24}$ alkyl and  
 $A_{30}$  is as defined for  $A_1$ ;

component II-i) is at least one compound of the formula XI-2



in which  
 $A_{31}$  is as defined for  $A_1$  and  
 $b_6$  is a number from 2 to 50;

component II-j) is at least one compound of the formula XII-2



in which

$A_{32}$  and  $A_{33}$  together form  $C_2-C_{14}$ alkylene,


$A_{34}$  is hydrogen or a group  $-G_1-COO-G_2$ ,

$G_1$  is  $C_2-C_{14}$ alkylene and

$G_2$  is  $C_1-C_{24}$ alkyl and

$A_{35}$  is as defined for  $A_1$ ;

component II-k) is at least one compound of the formula XIII-2




(XIII-2)

in which  $A_{36}$ ,  $A_{37}$ ,  $A_{38}$ ,  $A_{39}$  and  $A_{40}$  independently of one another are a direct bond or  $C_1-C_{10}$ alkylene,

$A_{41}$  is as defined for  $A_1$  and

$b_7$  is a number from 1 to 50;


component II-l) is at least one compound of the formula XIV-2



(XIV-2)


in which

$T_{12}$ ,  $T_{13}$  and  $T_{14}$  independently of one another are a group of the formula XV-2



in which L is a group of the formula III-2;

component II-m) is at least one compound of the formula XVI-2



in which  $\text{A}_{42}$  is hydrogen or methyl,

$\text{A}_{43}$  is a direct bond or  $\text{C}_1\text{-C}_{10}$ alkylene and

$b_8$  is a number from 2 to 50.

Examples of alkyl having up to 30 carbon atoms are methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, eicosyl, docosyl and triacontyl. One of the preferred definitions of  $\text{A}_1$ ,  $\text{A}_9$ ,  $\text{A}_{10}$ ,  $\text{A}_{18}$ ,  $\text{A}_{20}$ ,  $\text{A}_{22}$ ,  $\text{A}_{30}$ ,  $\text{A}_{31}$ ,  $\text{A}_{35}$  and  $\text{A}_{41}$  is  $\text{C}_1\text{-C}_4$ alkyl, especially methyl. One of the preferred definitions of  $\text{R}_{23}$ ,  $\text{R}_{27}$ ,  $\text{A}_{23}$  and  $\text{A}_{27}$  is  $\text{C}_1\text{-C}_{25}$ alkyl, especially  $\text{C}_{15}\text{-C}_{25}$ alkyl, for example hexadecyl and  $\text{C}_{18}\text{-C}_{22}$ alkyl. One of the preferred definitions of  $\text{R}_{25}$  and  $\text{A}_{25}$  is  $\text{C}_1\text{-C}_{25}$ alkyl, especially octadecyl. One of the preferred definitions of  $\text{R}_8$ ,  $\text{R}_{19}$ ,  $\text{A}_8$  and  $\text{A}_{19}$  is  $\text{C}_1\text{-C}_4$ alkyl, especially n-butyl.

Examples of  $\text{C}_5\text{-C}_{12}$ cycloalkyl are cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl and cyclododecyl.  $\text{C}_5\text{-C}_8$ Cycloalkyl, especially cyclohexyl, is preferred.

In a stabilizer mixture comprising component I-a) and component II-b) or II-m),  $\text{R}_1$  is preferably  $\text{C}_1\text{-C}_8$ cycloalkyl, especially cyclohexyl.

$\text{C}_1\text{-C}_4$ Alkyl-substituted  $\text{C}_5\text{-C}_{12}$ cycloalkyl is for example methylcyclohexyl or dimethylcyclohexyl.

-OH- and/or  $\text{C}_1\text{-C}_{10}$ alkyl-substituted phenyl is for example methylphenyl, dimethylphenyl, trimethylphenyl, tert-butylphenyl or 3,5-di-tert-butyl-4-hydroxyphenyl.

Examples of  $\text{C}_7\text{-C}_9$ phenylalkyl are benzyl and phenylethyl.



C<sub>7</sub>-C<sub>9</sub>Phenylalkyl which is substituted on the phenyl radical by -OH and/or by alkyl having up to 10 carbon atoms is for example methylbenzyl, dimethylbenzyl, trimethylbenzyl, tert-butylbenzyl or 3,5-di-tert-butyl-4-hydroxybenzyl.

Examples of C<sub>3</sub>-C<sub>6</sub>alkenyl are allyl, 2-methallyl, butenyl, pentenyl and hexenyl. Allyl is preferred. The carbon atom in position 1 is preferably saturated.


Examples of alkylene having up to 18 carbon atoms are methylene, ethylene, propylene, trimethylene, tetramethylene, pentamethylene, 2,2-dimethyltrimethylene, hexamethylene, trimethylhexamethylene, octamethylene and decamethylene. R<sub>12</sub> and A<sub>12</sub> are preferably hexamethylene, A<sub>43</sub> is preferably ethylene, R<sub>36</sub>, R<sub>38</sub>, A<sub>36</sub> and A<sub>38</sub> are preferably methylene, R<sub>39</sub> and A<sub>39</sub> are preferably 2,2-dimethylethylene and R<sub>40</sub> and A<sub>40</sub> are preferably 1,1-dimethylethylene.

An example of C<sub>4</sub>-C<sub>10</sub>alkanetetrayl is 1,2,3,4-butanetetrayl.

An example of C<sub>5</sub>-C<sub>7</sub>cycloalkylene is cyclohexylene.

An example of C<sub>1</sub>-C<sub>4</sub>alkylenedi(C<sub>5</sub>-C<sub>7</sub>cycloalkylene) is methylenedicyclohexylene.

Where the radicals R<sub>11</sub>, R<sub>12</sub>, R<sub>13</sub> or A<sub>11</sub>, A<sub>12</sub> and A<sub>13</sub>, together with the nitrogen atoms to which they are attached, form a 5- to 10-membered heterocyclic ring, this ring is for example



A 6-membered heterocyclic ring is preferred.

Where the radicals R<sub>14</sub> and R<sub>15</sub> or A<sub>14</sub> and A<sub>15</sub>, together with the nitrogen atom to which they are attached, form a 5- to 10-membered heterocyclic ring, this ring is for example 1-pyrrolidyl, piperidino, morpholino, 1-piperazinyl, 4-methyl-1-piperazinyl, 1-hexahydroazepinyl, 5,5,7-trimethyl-1-homopiperazinyl or 4,5,5,7-tetramethyl-1-homopiperazinyl. Morpholino is particularly preferred.

One of the preferred definitions of  $R_{23}$ ,  $R_{27}$ ,  $A_{23}$  and  $A_{27}$  is phenyl.

$Y_2$ ,  $E_2$ ,  $R_{37}$  and  $A_{37}$  are preferably a direct bond.

One of the preferred definitions of  $Y_1$ ,  $Y_3$ ,  $E_1$ ,  $E_3$ ,  $A_1$ ,  $A_9$ ,  $A_{10}$ ,  $A_{18}$ ,  $A_{20}$ ,  $A_{22}$ ,  $A_{30}$ ,  $A_{31}$ ,  $A_{35}$ ,  $A_{41}$  and  $A_{42}$  is hydrogen.

$n_2$  and  $b_2$  are preferably 2-25.

$n_3$  and  $b_3$  are preferably 1-25, especially 2-20 or 2-10.

$n_4'$ ,  $n_4''$ ,  $n_4'''$ ,  $b_4'$ ,  $b_4''$  and  $b_4'''$  are preferably 2-4.

$n_5$  and  $b_5$  are preferably 1-25, especially 1-20 or 1-10.

$n_6$  and  $b_6$  are preferably 2-25, especially 2-20 or 2-10.

$n_7$  and  $b_7$  are preferably 1-25, especially 1-20 or 1-10.

$b_8$  is preferably 2-25, especially 2-20 or 2-10.

In a stabilizer mixture comprising component I-a) and component II-b) or II-m),  $R_1$  is preferably other than  $C_1$ - $C_{18}$ alkyl, especially other than hydrogen and  $C_1$ - $C_{18}$ alkyl.

In a stabilizer mixture comprising component I-a) and component II-d), if  $R_1 = C_1$ - $C_{18}$ alkyl, the group  $-N(A_{14})A_{15}$  is preferably morpholino.

In a stabilizer mixture comprising component I-a) and component II-d), the group  $-N(A_{14})A_{15}$  is in particular morpholino.

The compounds described as components II-a) to II-m) are essentially known (in some cases commercially available) and can be prepared by known processes as described, for example, in US-A-3 640 928, US-A-4 108 829, US-A-3 925 376, US-A-4 086 204, US-A-4 331 586, US-A-5 051 458, US-A-4 477 615 and Chemical Abstracts - CAS No. 136 504-96-6, US-A-4 857 595, DD-A-262 439 (Derwent 89-122 983/17, Chemical Abstracts 111:58 964u), WO-A-94/12 544 (Derwent 94-177 274/22), US-A-4 356 307, US-A-4 340 534, US-A-4 408 051, US-A-4 689 416, US-A-4 110 334, US-A-4 529 760, US-A-5 182 390 (Chemical Abstracts - CAS No. 144 923-25-1) and US-A-4 233 412.

Component II-f) can be prepared analogously to known processes, for example by reacting a polyamine of formula VIII-2-a with cyanuric chloride in a molar ratio of from 1:2 to 1:4 in the presence of anhydrous lithium carbonate, sodium carbonate or potassium carbonate


in an organic solvent such as 1,2-dichloroethane, toluene, xylene, benzene, dioxane or tert-amyl alcohol at a temperature of from  $-20^{\circ}\text{C}$  to  $+10^{\circ}\text{C}$ , preferably from  $-10^{\circ}\text{C}$  to  $+10^{\circ}\text{C}$ , in particular from  $0^{\circ}\text{C}$  to  $+10^{\circ}\text{C}$ , for from 2 to 8 hours, followed by reaction of the resultant product with a 2,2,6,6-tetramethyl-4-piperidylamine of the formula VIII-2-b. The molar ratio of 2,2,6,6-tetramethyl-4-piperidylamine to polyamine of the formula VIII-2-a employed is for example from 4:1 to 8:1. The quantity of 2,2,6,6-tetramethyl-4-piperidylamine can be added in one portion or in more than one portion at intervals of a few hours.

The ratio of polyamine of the formula VIII-2-a to cyanuric chloride to 2,2,6,6-tetramethyl-4-piperidylamine of the formula VIII-2-b is preferably from 1:3:5 to 1:3:6.


The following example indicates one way of preparing the preferred component II-f).

Example: 23.6 g (0.128 mol) of cyanuric chloride, 7.43 g (0.0426 mol) of N,N'-bis[3-aminopropyl]ethylenediamine and 18 g (0.13 mol) of anhydrous potassium carbonate are reacted at  $5^{\circ}\text{C}$  for 3 hours with stirring in 250 ml of 1,2-dichloroethane. The mixture is warmed at room temperature for a further 4 hours. 27.2 g (0.128 mol) of N-(2,2,6,6-tetramethyl-4-piperidyl)butylamine are added and the resultant mixture is warmed at  $60^{\circ}\text{C}$  for 2 hours. A further 18 g (0.13 mol) of anhydrous potassium carbonate are added and the mixture is warmed at  $60^{\circ}\text{C}$  for a further 6 hours. The solvent is removed by distillation under a slight vacuum (200 mbar) and replaced by xylene. 18.2 g (0.085 mol) of N-(2,2,6,6-tetramethyl-4-piperidyl)butylamine and 5.2 g (0.13 mol) of ground sodium hydroxide are added, the mixture is heated at reflux for 2 hours and, for a further 12 hours, the water formed during the reaction is removed by azeotropic distillation. The mixture is filtered. The solution is washed with water and dried over  $\text{Na}_2\text{SO}_4$ . The solvent is evaporated and the residue is dried at  $120-130^{\circ}\text{C}$  in vacuo (0.1 mbar). Component II-f) is obtained as a colourless resin.


In general, component II-f) can for example be represented by a compound of the formula VIII-2-1, VIII-2-2 or VIII-2-3. It can also be in the form of a mixture of these three compounds.




(VIII-2-1)




(VIII-2-2)




A preferred definition of the formula VIII-2-1 is



A preferred definition of the formula VIII-2-2 is



A preferred definition of the formula VIII-2-3 is



In the above formulae VIII-2-1, VIII-2-2 and VIII-2-3,  $b_4$  is preferably from 1 to 20.

The compounds described as components I-a) to I-l) can be prepared from the compounds described as components II-a) to II-l) - the nitrogen atom in the 2,2,6,6-tetramethylpiperid-4-yl group being unsubstituted - in analogy to known processes, for example as disclosed in US-A-5 204 473, by oxidizing the corresponding 2,2,6,6-tetramethylpiperidine derivative with an appropriate peroxy compound, such as hydrogen peroxide or tert-butyl hydroperoxide, in the presence of a metal carbonyl or metal oxide catalyst, followed by reduction of the resulting oxyl intermediate to the desired N-hydroxyl derivative, preferably by catalytic hydrogenation.

After this, the O-alkyl derivatives can be synthesized in various ways. For example, the N-hydroxy derivative can be alkylated with sodium hydride and halogenated hydrocarbons, such as ethyl iodide. N-Methoxy variants can be prepared by thermolysis of a chlorobenzene solution of the nitroxyl radical and of di-tert-butyl peroxide. The product is formed by a coupling reaction between the nitroxyl radical and the methyl radical which is produced from the  $\beta$ -cleavage of a tert-butoxy radical.


Other N-alkoxy variants can be synthesized by coupling of nitroxyl radicals with hydrocarbon radicals, which are formed during the thermal decomposition of di-tert-butyl peroxide in the presence of hydrocarbon solvents, such as cyclohexane, toluene and ethylbenzene.

Although these procedures have been described with reference to N-alkoxy substituents, it will be understood that they can be employed equally to all  $OR_1$  groups.

For example, 1-cycloalkyloxy-2,2,6,6-tetramethylpiperid-4-yl derivatives can be prepared by reacting the corresponding 2,2,6,6-tetramethylpiperid-4-yl derivative with tert-butyl hydroperoxide in the presence of  $MoO_3$  and a cycloalkane.

In general, component I-f) can for example also be represented by a compound of the formula VIII-2-1, VIII-2-2 or VIII-2-3 in which the radicals  $A_{20}$  are a group  $-OR_{20}$ . It can also be in the form of a mixture of these three compounds.

The product described as component I-f) is, for example, also obtainable by reacting a product, obtained by reaction of a polyamine of the formula VIII-1-a with cyanuric chloride, with a compound of the formula VIII-1-b



in which

$n_4'$ ,  $n_4''$  and  $n_4'''$  independently of one another are a number from 2 to 12,

$\text{R}_{19}$  is hydrogen,  $\text{C}_1$ - $\text{C}_{12}$ alkyl,  $\text{C}_5$ - $\text{C}_{12}$ cycloalkyl, phenyl or  $\text{C}_7$ - $\text{C}_9$ phenylalkyl and

$\text{R}_{20}$  is as defined for  $\text{R}_1$ .

The reaction can take place, for example, in analogy to the preparation process described in US-A-4 477 615.


With particular preference, component I-a) is  $\text{®TINUVIN 123}$ , component II-a) is  $\text{®MARK LA 52}$  or  $\text{®MARK LA 57}$ , component II-b) is  $\text{®CHIMASSORB 119}$ , component II-d) is  $\text{®CHIMASSORB 944}$ ,  $\text{®CYASORB UV 3346}$  or  $\text{®DASTIB 1082}$ , component II-e) is  $\text{®UVASIL 299}$  or  $\text{®UVASIL 125}$ , component II-f) is  $\text{®UVASORB HA 88}$ , component II-g) is  $\text{®UVINUL 5050 H}$ ,  $\text{®LICHTSCHUTZSTOFF UV 31}$  or  $\text{®LUCHEM HA-B 18}$ , component II-i) is  $\text{®HOSTAVIN N 30}$ , component II-k) is  $\text{®MARK LA 63}$  or  $\text{®MARK LA 68}$  and component II-m) is  $\text{®TINUVIN 622}$ .

Other products which can be employed, for example, are as component II-a)  $\text{®Tinuvin 770}$  or  $\text{®DASTIB 845}$ , as component II-h)  $\text{®LICHTSCHUTZMITTEL S 95}$  and as component II-j)  $\text{®HOSTAVIN N 20}$  or  $\text{®SANDUVOR 3050}$ .

As component I-f) it is preferred to employ  $\text{®UVASORB HA 88}$ , in which the 2,2,6,6-tetramethylpiperidin-4-yl radicals are replaced by a group of the formula VIII-1-c.

If the radical  $\text{A}_{31}$  in the compound of the formula XI-2 is hydrogen, this compound can be in the form of a mixture with a compound of the formula XI-2\*







and can also be employed as such a mixture, as component II-i), in the stabilizer system of the invention. The ratio of XI-2:XI-2\* is for example from 20:1 to 1:20 or from 1:10 to 10:1.

The definitions of the terminal groups which saturate the free valences in the compounds of the formulae VI-1, VI-2, VII-1, VII-2, VIII-2-1, VIII-2-2, VIII-2-3, IX-1, IX-2, XI-1, XI-2, XI-2\*, XIII-1, XIII-2 and XVI-2 depend on the processes used for their preparation. The terminal groups can also be modified after the preparation of the compounds.


If the compounds of the formula VI-1 are prepared by reacting a compound of the formula




in which X is for example halogen, especially chlorine, and  $\text{R}_{14}$  and  $\text{R}_{15}$  are as defined above, with a compound of the formula



in which  $\text{R}_{11}$ ,  $\text{R}_{12}$  and  $\text{R}_{13}$  are as defined above, then the terminal group bonded to the diamino radical is hydrogen or



and the terminal group bonded to the triazine radical is X or




If X is a halogen, it is advantageous to replace it, for example, by -OH or an amino group when the reaction is complete. Examples of amino groups which may be mentioned are pyrrolidin-1-yl, morpholino, -NH<sub>2</sub>, -N(C<sub>1</sub>-C<sub>8</sub>alkyl)<sub>2</sub> and -NR(C<sub>1</sub>-C<sub>8</sub>alkyl), in which R is hydrogen or a group of the formula IV-1.

The comments made above regarding the compounds of the formula VI-1 can be applied correspondingly to the compounds of the formula VI-2, the radicals R<sub>11</sub>, R<sub>12</sub>, R<sub>13</sub>, R<sub>14</sub> and R<sub>15</sub> corresponding to the respective radicals A<sub>11</sub>, A<sub>12</sub>, A<sub>13</sub>, A<sub>14</sub> and A<sub>15</sub> and the group IV-1 corresponding to the group IV-2.


In the compounds of the formula VII-1 or VII-2 the terminal group bonded to the silicon atom can for example be (R<sub>16</sub>)<sub>3</sub>Si-O- or (A<sub>16</sub>)<sub>3</sub>Si-O- and the terminal group bonded to the oxygen can for example be -Si(R<sub>16</sub>)<sub>3</sub> or -Si(A<sub>16</sub>)<sub>3</sub>.

The compounds of the formulae VII-1 and VII-2 can also be in the form of cyclic compounds if n<sub>3</sub> or b<sub>3</sub> is a number from 3 to 10; in other words, the free valences represented in the structural formulae in that case form a direct bond.


In the compounds of the formulae VIII-2-1, VIII-2-2 and VIII-2-3 the terminal group bonded to the triazine radical is for example Cl or a group




and the terminal group bonded to the amino radical is for example hydrogen or a group



In the compounds of the formula IX-1, the terminal group bonded to the 2,5-dioxopyrrolidine ring is for example hydrogen and the terminal group bonded to the radical  $-C(R_{27})(R_{28})-$  is for example




In the compounds of the formula IX-2 the terminal group bonded to the 2,5-dioxopyrrolidine ring is for example hydrogen and the terminal group bonded to the radical  $-C(A_{27})(A_{28})-$  is for example




In the compounds of the formula XI-1 and XI-2 the terminal group bonded to the dimethylene radical can for example be -OH and the terminal group bonded to the oxygen can for example be hydrogen. The terminal groups can also be polyether radicals.


In the compounds of the formula XI-2\*, the terminal group bonded to the nitrogen can for example be hydrogen and the terminal group bonded to the 2-hydroxypropylene radical can for example be a group




In the compounds of the formula XIII-1, the terminal group bonded to the carbonyl radical is for example




and the terminal group bonded to the oxygen radical is for example




In the compounds of the formula XIII-2 the terminal group bonded to the carbonyl radical is for example



and the terminal group bonded to the oxygen radical is for example




Where the preparation of the compounds of the formula XVI-2 takes place, for example, by reacting a compound of the formula



in which  $A_{42}$  is as defined above, with a dicarboxylic diester of the formula  $Q-OOC-A_{43}-COO-Q$ , in which  $Q$  is for example methyl, ethyl or propyl and  $A_{43}$  is as defined above, the terminal group bonded to the 2,2,6,6-tetramethyl-4-oxypiperidin-1-yl

radical is hydrogen or  $-\text{CO}-\text{A}_{43}-\text{COO}-\text{Q}$  and the terminal group bonded to the diacyl radical is  $-\text{O}-\text{Q}$  or



A preferred stabilizer mixture is one in which  $\text{R}_1$ ,  $\text{R}_9$ ,  $\text{R}_{10}$ ,  $\text{R}_{18}$ ,  $\text{R}_{20}$ ,  $\text{R}_{22}$ ,  $\text{R}_{30}$ ,  $\text{R}_{31}$ ,  $\text{R}_{35}$  and  $\text{R}_{41}$  independently of one another are  $\text{C}_1$ - $\text{C}_{12}$ alkyl,  $\text{C}_5$ - $\text{C}_8$ cycloalkyl or methyl-substituted  $\text{C}_5$ - $\text{C}_8$ cycloalkyl.

Preference is likewise given to a stabilizer mixture in which  $\text{R}_1$ ,  $\text{R}_9$ ,  $\text{R}_{10}$ ,  $\text{R}_{18}$ ,  $\text{R}_{20}$ ,  $\text{R}_{22}$ ,  $\text{R}_{30}$ ,  $\text{R}_{31}$ ,  $\text{R}_{35}$  and  $\text{R}_{41}$  independently of one another are methyl, octyl or cyclohexyl.

Also of interest is a stabilizer mixture in which  $\text{A}_1$ ,  $\text{A}_9$ ,  $\text{A}_{10}$ ,  $\text{A}_{18}$ ,  $\text{A}_{20}$ ,  $\text{A}_{22}$ ,  $\text{A}_{30}$ ,  $\text{A}_{31}$ ,  $\text{A}_{35}$  and  $\text{A}_{41}$  independently of one another are hydrogen or methyl.

A preferred embodiment corresponds also to a stabilizer mixture comprising a component I-a), I-b), I-c), I-d), I-e), I-f), I-g), I-h), I-i), I-j), I-k) or I-l) and a component II-a), II-b), II-d), II-e), II-f), II-g), II-i), II-k) or II-m).

The following stabilizer mixtures may be mentioned as examples:

1. stabilizer mixture comprising a component I-a) and a component II-b), II-d) or II-m),
2. stabilizer mixture comprising a component I-b) and a component II-b), II-d) or II-m) and
3. stabilizer mixture comprising a component I-c) and a component II-b), II-d) or II-m).

Also preferred is a stabilizer mixture

in which  $n_1$  is 1, 2 or 4,

if  $n_1$  is 1,  $\text{R}_2$  is  $\text{C}_{10}$ - $\text{C}_{20}$ alkyl,

if  $n_1$  is 2,  $\text{R}_2$  is  $\text{C}_6$ - $\text{C}_{10}$ alkylene and

if  $n_1$  is 4,  $\text{R}_2$  is butanetetrayl;

$\text{R}_3$  and  $\text{R}_7$  independently of one another are hydrogen or  $\text{C}_1$ - $\text{C}_4$ alkyl,

$\text{R}_4$ ,  $\text{R}_5$  and  $\text{R}_6$  independently of one another are  $\text{C}_2$ - $\text{C}_6$ alkylene,

$\text{R}_8$  is hydrogen,  $\text{C}_1$ - $\text{C}_6$ alkyl,  $\text{C}_5$ - $\text{C}_8$ cycloalkyl, methyl-substituted  $\text{C}_5$ - $\text{C}_8$ cycloalkyl,

phenyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl or a group of the formula IV-1;

R<sub>11</sub>, R<sub>13</sub>, R<sub>14</sub> and R<sub>15</sub> independently of one another are hydrogen, C<sub>1</sub>-C<sub>8</sub>alkyl, C<sub>5</sub>-C<sub>8</sub>cycloalkyl, methyl-substituted C<sub>5</sub>-C<sub>8</sub>cycloalkyl, phenyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl or a group of the formula IV-1, or the radicals R<sub>14</sub> and R<sub>15</sub>, together with the nitrogen atom to which they are attached, form a 6-membered heterocyclic ring, R<sub>12</sub> is C<sub>2</sub>-C<sub>10</sub>alkylene and n<sub>2</sub> is a number from 2 to 25;

R<sub>16</sub> is C<sub>1</sub>-C<sub>4</sub>alkyl, C<sub>5</sub>-C<sub>8</sub>cycloalkyl or phenyl, R<sub>17</sub> is C<sub>3</sub>-C<sub>6</sub>alkylene and n<sub>3</sub> is a number from 1 to 25;

n<sub>4</sub>', n<sub>4</sub>'' and n<sub>4</sub>''' independently of one another are a number from 2 to 4 and R<sub>19</sub> is C<sub>1</sub>-C<sub>4</sub>alkyl;

R<sub>21</sub> and R<sub>26</sub> independently of one another are a direct bond or a group -N(Y<sub>1</sub>)-CO-Y<sub>2</sub>-CO-N(Y<sub>3</sub>)-, Y<sub>1</sub> and Y<sub>3</sub> independently of one another are hydrogen or C<sub>1</sub>-C<sub>4</sub>alkyl, Y<sub>2</sub> is a direct bond, R<sub>23</sub> and R<sub>27</sub> are C<sub>1</sub>-C<sub>25</sub>alkyl or phenyl, R<sub>24</sub> and R<sub>28</sub> are hydrogen or C<sub>1</sub>-C<sub>4</sub>alkyl, R<sub>25</sub> is C<sub>1</sub>-C<sub>25</sub>alkyl or a group of the formula IV-1 and n<sub>5</sub> is a number from 1 to 25;

R<sub>29</sub> is C<sub>8</sub>-C<sub>15</sub>alkyl;




n<sub>6</sub> is a number from 2 to 25;

R<sub>32</sub> and R<sub>33</sub> together form C<sub>8</sub>-C<sub>14</sub>alkylene, R<sub>34</sub> is hydrogen or a group -Z<sub>1</sub>-COO-Z<sub>2</sub>, Z<sub>1</sub> is C<sub>2</sub>-C<sub>6</sub>alkylene and Z<sub>2</sub> is C<sub>8</sub>-C<sub>15</sub>alkyl;

R<sub>36</sub>, R<sub>38</sub>, R<sub>39</sub> and R<sub>40</sub> independently of one another are C<sub>1</sub>-C<sub>4</sub>alkylene,

$R_{37}$  is a direct bond and  
 $n_7$  is a number from 1 to 25.


Particular preference is given to a stabilizer mixture in which  
 component I-a) is at least one compound of the formula I-1-a-1, I-1-a-2 or I-1-a-3



in which  $R_1$  is methyl, octyl or cyclohexyl;


component I-b) is at least one compound of the formula II-1-b






in which  $R_9$  is as defined for  $R_1$ ;

component I-c) is at least one compound of the formula V-1-c




in which  $R_9$  is as defined above;


component I-d) is at least one compound of the formula VI-1-d-1, VI-1-d-2 or VI-1-d-3



(VI-1-d-1)




(VI-1-d-2)



(VI-1-d-3)

in which  $R_{10}$  is as defined for  $R_1$  and  $n_2$  is a number from 2 to 25;


component I-e) is at least one compound of the formula VII-1-e




in which  $\text{R}_{18}$  is as defined for  $\text{R}_1$  and  $n_3$  is a number from 1 to 25;

component I-f) is a product obtainable by

a) reacting a product, obtained by reaction of a polyamine of the formula






with cyanuric chloride, with a compound of the formula



b) further reacting the 2,2,6,6-tetramethylpiperid-4-yl groups which are present in the molecule to give groups of the formula VIII-1-c;


component 1-g) is at least one compound of the formula IX-1-g-1, IX-1-g-2 or IX-1-g-3





in which  $R_{10}$  and  $R_{22}$  are as defined for  $R_1$  and  $n_5$  is a number from 1 to 25;

component 1-h) is at least one compound of the formula X-1-h





in which  $R_{30}$  is as defined for  $R_1$ ;

component I-i) is at least one compound of the formula (XI-1) in which  $R_3$  is as defined


for  $R_1$  and  $n_6$  is a number from 2 to 25;

component I-j) is at least one compound of the formula XII-1-j-1 or XII-1-j-2 .




in which  $R_{35}$  is as defined for  $R_1$ ;

component I-k) is at least one compound of the formula XIII-1-k



in which  $R_4$  is as defined for  $R_1$  and  $n_7$  is a number from 1 to 25;

component I-1) is at least one compound of the formula XIV-1-1



in which  $R_9$  is as defined for  $R_1$ .

Preference is furthermore given to a stabilizer mixture

in which  $b_1$  is 1, 2 or 4,

if  $b_1$  is 1,  $A_2$  is  $C_{10}$ - $C_{20}$ alkyl,

if  $b_1$  is 2,  $A_2$  is  $C_6$ - $C_{10}$ alkylene and

if  $b_1$  is 4,  $A_2$  is butanetetrayl;

$A_3$  and  $A_7$  independently of one another are hydrogen or  $C_1$ - $C_4$ alkyl,

$A_4$ ,  $A_5$  and  $A_6$  independently of one another are  $C_2$ - $C_6$ alkylene,

$A_8$  is hydrogen,  $C_1$ - $C_6$ alkyl,  $C_5$ - $C_8$ cycloalkyl, methyl-substituted  $C_5$ - $C_8$ cycloalkyl, phenyl,  $C_7$ - $C_9$ phenylalkyl or a group of the formula IV-2;

$A_{11}$ ,  $A_{13}$ ,  $A_{14}$  and  $A_{15}$  independently of one another are hydrogen,  $C_1$ - $C_8$ alkyl,

$C_5$ - $C_8$ cycloalkyl, methyl-substituted  $C_5$ - $C_8$ cycloalkyl, phenyl,  $C_7$ - $C_9$ phenylalkyl or a group of the formula IV-2, or

the radicals  $A_{14}$  and  $A_{15}$ , together with the nitrogen atom to which they are attached, form a 6-membered heterocyclic ring,

$A_{12}$  is  $C_2$ - $C_{10}$ alkylene and

$b_2$  is a number from 2 to 25;

$A_{16}$  is  $C_1$ - $C_4$ alkyl,  $C_5$ - $C_8$ cycloalkyl or phenyl,

$A_{17}$  is  $C_3$ - $C_6$ alkylene and

$b_3$  is a number from 1 to 25;

$b_4'$ ,  $b_4''$  and  $b_4'''$  independently of one another are a number from 2 to 4 and

$A_{19}$  is  $C_1$ - $C_4$ alkyl;

$A_{21}$  and  $A_{26}$  independently of one another are a direct bond or a group

$-N(E_1)-CO-E_2-CO-N(E_3)-$ ,

$E_1$  and  $E_3$  independently of one another are hydrogen or  $C_1-C_4$ alkyl,

$E_2$  is a direct bond,

$A_{23}$  and  $A_{27}$  are  $C_1-C_{25}$ alkyl or phenyl,

$A_{24}$  and  $A_{28}$  are hydrogen or  $C_1-C_4$ alkyl,

$A_{25}$  is  $C_1-C_{25}$ alkyl or a group of the formula IV-2 and

$b_5$  is a number from 1 to 25;

$A_{29}$  is  $C_8-C_{15}$ alkyl;

$b_6$  is a number from 2 to 25;

$A_{32}$  and  $A_{33}$  together form  $C_8-C_{14}$ alkylene,

$A_{34}$  is hydrogen or a group  $-G_1-COO-G_2$ ,

$G_1$  is  $C_2-C_6$ alkylene and


$G_2$  is  $C_8-C_{15}$ alkyl;

$A_{36}$ ,  $A_{38}$ ,  $A_{39}$  and  $A_{40}$  independently of one another are  $C_1-C_4$ alkylene,

$A_{37}$  is a direct bond and


$b_7$  is a number from 1 to 25.

Particular preference is given to a stabilizer mixture in which component II-a) is at least one compound of the formula I-2-a-3





in which  $A_1$  is hydrogen or methyl;

component II-b) is at least one compound of the formula II-2-b




in which  $A_9$  is as defined for  $A_1$ ;

component II-d) is at least one compound of the formula VI-2-d-1, VI-2-d-2 or VI-2-d-3








(VI-2-d-3)

in which  $A_{10}$  is as defined for  $A_1$  and  $b_2$  is a number from 2 to 25;


component II-e) is at least one compound of the formula VI-2-e




(VI-2-e)

in which  $A_{18}$  is as defined for  $A_1$  and  $b_3$  is a number from 1 to 25;

component II-f) is a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula






with cyanuric chloride, with a compound of the formula



in which  $A_{20}$  is as defined for  $A_1$ ;


component II-g) is at least one compound of the formula IX-2-g-1, IX-2-g-2 or IX-2-g-3



in which  $A_{10}$  and  $A_{22}$  are as defined for  $A_1$  and  $b_5$  is a number from 1 to 25;


component II-i) is at least one compound of the formula XI-2 in which  $A_{31}$  is as defined for  $A_1$  and  $b_6$  is a number from 2 to 25;

component II-k) is at least one compound of the formula XIII-2-k



in which  $A_{41}$  is as defined for  $A_1$  and  $b_7$  is a number from 1 to 25;

component II-m) is at least one compound of the formula XVI-2-m




in which  $b_8$  is a number from 2 to 25.


Particular interest attaches to the following stabilizer systems:

- a) stabilizer mixture comprising at least one compound of the formula I-1-a-1 in which  $R_1$  is cyclohexyl, and at least one compound of the formula XVI-2-m,
- b) stabilizer mixture comprising at least one compound of the formula I-1-a-1 in which  $R_1$  is cyclohexyl, and at least one compound of the formula VI-2-d-1 in which  $A_{10}$  is hydrogen,
- c) stabilizer mixture comprising at least one compound of the formula I-1-a-1 in which  $R_1$  is cyclohexyl, and at least one compound of the formula II-2-b in which  $A_9$  is methyl,
- d) stabilizer mixture comprising at least one compound of the formula II-1-b in which  $R_9$  is cyclohexyl, and at least one compound of the formula XVI-2-m,
- e) stabilizer mixture comprising at least one compound of the formula II-1-b in which  $R_9$  is cyclohexyl, and at least one compound of the formula VI-2-d-1 in which  $A_{10}$  is hydrogen,
- f) stabilizer mixture comprising at least one compound of the formula II-1-b in which  $R_9$  is cyclohexyl, and at least one compound of the formula II-2-b in which  $A_9$  is methyl,

- g) stabilizer mixture comprising at least one compound of the formula V-1-c in which  $R_9$  is cyclohexyl, and at least one compound of the formula XVI-2-m,
- h) stabilizer mixture comprising at least one compound of the formula V-1-c in which  $R_9$  is cyclohexyl, and at least one compound of the formula VI-2-d-1 in which  $A_{10}$  is hydrogen,
- i) stabilizer mixture comprising at least one compound of the formula V-1-c in which  $R_9$  is cyclohexyl, and at least one compound of the formula II-2-b in which  $A_9$  is methyl,
- j) stabilizer mixture comprising at least one compound of the formula V-1-c in which  $R_9$  is methyl, and at least one compound of the formula XVI-2-m,
- k) stabilizer mixture comprising at least one compound of the formula V-1-c in which  $R_9$  is methyl, and at least one compound of the formula VI-2-d-1 in which  $A_{10}$  is hydrogen,
- l) stabilizer mixture comprising at least one compound of the formula V-1-c in which  $R_9$  is methyl, and at least one compound of the formula II-2-b in which  $A_9$  is methyl,
- m) stabilizer mixture comprising at least one compound of the formula I-1-a-1 in which  $R_1$  is octyl, and at least one compound of the formula VI-2-d-2 in which  $A_{10}$  is hydrogen,
- n) stabilizer mixture comprising at least one compound of the formula I-1-a-1 in which  $R_1$  is octyl, and a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula



with cyanuric chloride, with a compound of the formula



In the abovementioned stabilizer systems, the two components are particularly preferably in a weight ratio of from 1:4 to 1:1.

The novel stabilizer mixture is suitable for stabilizing organic materials against thermal, oxidative or light-induced degradation. Examples of such materials are the following:

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, poly-4-methylpent-1-ene, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), high den-

sity and high molecular weight polyethylene (HDPE-HMW), high density and ultrahigh molecular weight polyethylene (HDPE-UHMW), medium density polyethylene (MDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), branched low density polyethylene (BLDPE).

Polyolefins, i.e. the polymers of monoolefins exemplified in the preceding paragraph, preferably polyethylene and polypropylene, can be prepared by different, and especially by the following, methods:

- a) radical polymerisation (normally under high pressure and at elevated temperature).
  - b) catalytic polymerisation using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either  $\pi$ - or  $\sigma$ -coordinated. These metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used, typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, IIa and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler (-Natta), TNZ (DuPont), metallocene or single site catalysts (SSC).
2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).
  3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene/propylene copolymers, linear low density polyethylene (LLDPE) and mixtures thereof with low density polyethylene (LDPE), propylene/but-1-ene copolymers, propylene/isobutylene copolymers, ethylene/but-1-ene copolymers, ethylene/hexene copolymers, ethylene/methylpentene copolymers, ethylene/heptene

copolymers, ethylene/octene copolymers, propylene/butadiene copolymers, isobutylene/isoprene copolymers, ethylene/alkyl acrylate copolymers, ethylene/alkyl methacrylate copolymers, ethylene/vinyl acetate copolymers and their copolymers with carbon monoxide or ethylene/acrylic acid copolymers and their salts (ionomers) as well as terpolymers of ethylene with propylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene; and mixtures of such copolymers with one another and with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers, LDPE/ethylene-vinyl acetate copolymers (EVA), LDPE/ethylene-acrylic acid copolymers (EAA), LLDPE/EVA, LLDPE/EAA and alternating or random polyalkylene/carbon monoxide copolymers and mixtures thereof with other polymers, for example polyamides.

4. Hydrocarbon resins (for example  $C_5$ - $C_9$ ) including hydrogenated modifications thereof (e.g. tackifiers) and mixtures of polyalkylenes and starch.

5. Polystyrene, poly(p-methylstyrene), poly( $\alpha$ -methylstyrene).

6. Copolymers of styrene or  $\alpha$ -methylstyrene with dienes or acrylic derivatives, for example styrene/butadiene, styrene/acrylonitrile, styrene/alkyl methacrylate, styrene/butadiene/alkyl acrylate, styrene/butadiene/alkyl methacrylate, styrene/maleic anhydride, styrene/acrylonitrile/methyl acrylate; mixtures of high impact strength of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene/propylene/diene terpolymer; and block copolymers of styrene such as styrene/butadiene-styrene, styrene/isoprene/styrene, styrene/ethylene/butylene/styrene or styrene/ethylene-propylene/styrene.

7. Graft copolymers of styrene or  $\alpha$ -methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile copolymers; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene; styrene and alkyl acrylates or methacrylates on polybutadiene; styrene and acrylonitrile on ethylene/propylene/diene terpolymers; styrene and acrylonitrile on polyalkyl acrylates or polyalkyl methacrylates, styrene and acrylonitrile on acrylate/butadiene copolymers, as well as mixtures thereof with the copolymers listed under 6), for example the copolymer mixtures known as ABS, MBS, ASA or AES polymers.

8. Halogen-containing polymers such as polychloroprene, chlorinated rubbers, chlorinated

and brominated copolymer of isobutylene-isoprene (halobutyl rubber), chlorinated or sulfochlorinated polyethylene, copolymers of ethylene and chlorinated ethylene, epichlorohydrin homo- and copolymers, especially polymers of halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof such as vinyl chloride/vinylidene chloride, vinyl chloride/vinyl acetate or vinylidene chloride/vinyl acetate copolymers.

9. Polymers derived from  $\alpha,\beta$ -unsaturated acids and derivatives thereof such as polyacrylates and polymethacrylates; polymethyl methacrylates, polyacrylamides and polyacrylonitriles, impact-modified with butyl acrylate.

10. Copolymers of the monomers mentioned under 9) with each other or with other unsaturated monomers, for example acrylonitrile/ butadiene copolymers, acrylonitrile/-alkyl acrylate copolymers, acrylonitrile/alkoxyalkyl acrylate or acrylonitrile/vinyl halide copolymers or acrylonitrile/ alkyl methacrylate/butadiene terpolymers.

11. Polymers derived from unsaturated alcohols and amines or the acyl derivatives or acetals thereof, for example polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallyl melamine; as well as their copolymers with olefins mentioned in 1) above.

12. Homopolymers and copolymers of cyclic ethers such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.

13. Polyacetals such as polyoxymethylene and those polyoxymethylenes which contain ethylene oxide as a comonomer; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.

14. Polyphenylene oxides and sulfides, and mixtures of polyphenylene oxides with styrene polymers or polyamides.

15. Polyurethanes derived from hydroxyl-terminated polyethers, polyesters or polybutadienes on the one hand and aliphatic or aromatic polyisocyanates on the other, as well as precursors thereof.

16. Polyamides and copolyamides derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, for example polyamide 4, poly-

amide 6, polyamide 6/6, 6/10, 6/9, 6/12, 4/6, 12/12, polyamide 11, polyamide 12, aromatic polyamides starting from m-xylene diamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic or/and terephthalic acid and with or without an elastomer as modifier, for example poly-2,4,4'-trimethylhexamethylene terephthalamide or poly-m-phenylene isophthalamide; and also block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, e.g. with polyethylene glycol, polypropylene glycol or polytetramethylene glycol; as well as polyamides or copolyamides modified with EPDM or ABS; and polyamides condensed during processing (RIM polyamide systems).

17. Polyureas, polyimides, polyamide-imides, polyetherimids, polyesterimids, polyhydantoins and polybenzimidazoles.

18. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids or the corresponding lactones, for example polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylolcyclohexane terephthalate and polyhydroxybenzoates, as well as block copolyether esters derived from hydroxyl-terminated polyethers; and also polyesters modified with polycarbonates or MBS.

19. Polycarbonates and polyester carbonates.

20. Polysulfones, polyether sulfones and polyether ketones.

21. Crosslinked polymers derived from aldehydes on the one hand and phenols, ureas and melamines on the other hand, such as phenol/formaldehyde resins, urea/formaldehyde resins and melamine/formaldehyde resins.

22. Drying and non-drying alkyd resins.

23. Unsaturated polyester resins derived from copolyesters of saturated and unsaturated dicarboxylic acids with polyhydric alcohols and vinyl compounds as crosslinking agents, and also halogen-containing modifications thereof of low flammability.

24. Crosslinkable acrylic resins derived from substituted acrylates, for example epoxy acrylates, urethane acrylates or polyester acrylates.

25. Alkyd resins, polyester resins and acrylate resins crosslinked with melamine resins,



urea resins, isocyanates, isocyanurates, polyisocyanates or epoxy resins.

26. Crosslinked epoxy resins derived from aliphatic, cycloaliphatic, heterocyclic or aromatic glycidyl compounds, e.g. products of diglycidyl ethers of bisphenol A and bisphenol F, which are crosslinked with customary hardeners such as anhydrides or amines, with or without accelerators.

27. Natural polymers such as cellulose, rubber, gelatin and chemically modified homologous derivatives thereof, for example cellulose acetates, cellulose propionates and cellulose butyrates, or the cellulose ethers such as methyl cellulose; as well as rosins and their derivatives.

28. Blends of the aforementioned polymers (polyblends), for example PP/EPDM, Polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS, PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, PA/PPO, PBT/PC/ABS or PBT/PET/PC.

29. Naturally occurring and synthetic organic materials which are pure monomeric compounds or mixtures of such compounds, for example mineral oils, animal and vegetable fats, oil and waxes, or oils, fats and waxes based on synthetic esters (e.g. phthalates, adipates, phosphates or trimellitates) and also mixtures of synthetic esters with mineral oils in any weight ratios, typically those used as spinning compositions, as well as aqueous emulsions of such materials.

30. Aqueous emulsions of natural or synthetic rubber, e.g. natural latex or latices of carboxylated styrene/butadiene copolymers.

The invention therefore additionally relates to a composition comprising an organic material which is sensitive to oxidative, thermal or light-induced degradation and a novel stabilizer mixture.

The organic material is preferably a synthetic polymer, in particular from one of the above groups. Polyolefins are preferred and polyethylene, polypropylene and copolymers thereof are particularly preferred.

The components of the novel stabilizer system can be added to the material to be

stabilized either individually or mixed with one another. In this context, component I-a), I-b), I-c), I-d), I-e), I-f), I-g), I-h), I-i), I-j), I-k) or I-l) can be employed in a quantity of from 0.01 to 2.5 %, preferably from 0.05 to 0.5 %, and component II-a), II-b), II-c), II-d), II-e), II-f), II-g), II-h), II-i), II-j), II-k), II-l) or II-m) can be employed in a quantity of from 0.01 to 4.99 %, preferably from 0.05 to 1.5 %, with the proviso that the total quantity of component I-a), I-b), I-c), I-d), I-e), I-f), I-g), I-h), I-i), I-j), I-k) or I-l) and component II-a), II-b), II-c), II-d), II-e), II-f), II-g), II-h), II-i), II-j), II-k), II-l) or II-m) is from 0.02 to 5 %, based on the overall weight of the material to be stabilized.

The total quantity of component I-a), I-b), I-c), I-d), I-e), I-f), I-g), I-h), I-i), I-j), I-k) or I-l) and component II-a), II-b), II-c), II-d), II-e), II-f), II-g), II-h), II-i), II-j), II-k), II-l) or II-m) is preferably from 0.05 to 3 %, in particular from 0.05 to 2 % or from 0.05 to 1 %, based on the overall weight of the material to be stabilized.

The weight ratio of component I-a), I-b), I-c), I-d), I-e), I-f), I-g), I-h), I-i), I-j), I-k) or I-l) to component II-a), II-b), II-c), II-d), II-e), II-f), II-g), II-h), II-i), II-j), II-k), II-l) or II-m) is preferably from 20:1 to 1:20, in particular from 10:1 to 1:10, for example from 1:5 to 5:1 or from 1:4 to 1:1.

The novel stabilizer mixture or the individual components can be incorporated into the organic material by known methods, for example before or during shaping or by applying the dissolved or dispersed compounds to the organic material, if desired with subsequent evaporation of the solvent. The individual components of the novel stabilizer mixture can be added to the materials to be stabilized in the form of a powder, as granules or as a masterbatch, which contains these components in, for example, a concentration of from 2.5 to 25 % by weight.

If desired, before incorporation, the components of the novel stabilizer system can be mixed with one another in a melt (melt blending).

The novel stabilizer system or its components can be added before or during polymerization or prior to crosslinking.

The materials stabilized in this way can be employed in a wide variety of forms, for example as films, fibres, tapes, moulding compositions or profiles or as binders for coatings, adhesives or putties.

The stabilized organic materials of the invention can additionally comprise various conventional additives, for example:

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-( $\alpha$ -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, nonylphenols which are linear or branched in the side chains, for example, 2,6-di-nonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)phenol and mixtures thereof.

1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-di-decylthiomethyl-4-nonylphenol.

1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-di-phenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis-(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

1.4. Tocopherols, for example  $\alpha$ -tocopherol,  $\beta$ -tocopherol,  $\gamma$ -tocopherol,  $\delta$ -tocopherol and mixtures thereof (Vitamin E).

1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol), 4,4'-thiobis-(3,6-di-sec-amylphenol), 4,4'-bis-(2,6-dimethyl-4-hydroxyphenyl) disulfide.

1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-( $\alpha$ -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methyl-

lenebis[6-( $\alpha$ -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-( $\alpha,\alpha$ -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis-(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra-(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

1.7. O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxy-dibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzylmercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)-amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithioterephthalate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isooctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.

1.8. Hydroxybenzylated malonates, for example dioctadecyl-2,2-bis-(3,5-di-tert-butyl-2-hydroxybenzyl)-malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)-malonate, di-dodecylmercaptoethyl-2,2-bis-(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis-[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

1.9. Aromatic hydroxybenzyl compounds, for example 1,3,5-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10. Triazine Compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphos-

phonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-5-tert-butyl-4-hydroxy-3-methylbenzylphosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzylphosphonic acid.

1.12. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.13. Esters of  $\beta$ -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.14. Esters of  $\beta$ -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.15. Esters of  $\beta$ -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.17. Amides of  $\beta$ -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine.

1.18. Ascorbic acid (vitamin C)

1.19. Aminic antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfamoyl)-diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxydiphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylamino-phenol, 4-nonanoylamino-phenol, 4-dodecanoylamino-phenol, 4-octadecanoylamino-phenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methylphenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, Bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated nonyldiphenylamines, a mixture of mono- and dialkylated dodecyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, a mixture of mono- und dialkylated tert-butyldiphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, a mixture of mono- und dialkylated tert-butyl/tert-octylphenothiazines, a mixture of mono- und dialkylated tert-octylphenothiazines, N-allylphenothiazin, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis(2,2,6,6-tetramethyl-piperid-4-yl)-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl)sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)-

benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chloro-benzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis-( $\alpha,\alpha$ -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, mixture of 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)-carbonylethyl]-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, and 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonylethyl)phenyl)benzotriazole, 2,2'-methylene-bis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-ylphenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonylethyl)-2'-hydroxyphenyl]-2H-benzotriazole with polyethylene glycol 300;  $[R-CH_2CH_2-COO(CH_2)_3]_n$ , where R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted and unsubstituted benzoic acids, as for example 4-tertbutylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl) resorcinol, benzoyl resorcinol, 2,4-di-tertbutylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl  $\alpha$ -cyano- $\beta,\beta$ -diphenylacrylate, isooctyl  $\alpha$ -cyano- $\beta,\beta$ -diphenylacrylate, methyl  $\alpha$ -carbomethoxycinnamate, methyl  $\alpha$ -cyano- $\beta$ -methyl-p-methoxycinnamate, butyl  $\alpha$ -cyano- $\beta$ -methyl-p-methoxy-cinnamate, methyl  $\alpha$ -carbomethoxy-p-methoxycinnamate and N-( $\beta$ -carbomethoxy- $\beta$ -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thio-bis-[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands

such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutylthiocarbamate, nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenyl undecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(2,2,6,6-tetramethyl-4-piperidyl)succinate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-4-piperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, the condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl)nitrilotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butane-tetracarboxylate, 1,1'-(1,2-ethanediyl)bis(3,3,5,5-tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearoxy-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decan-2,4-dione, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate, the condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidin-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidine-2,5-dione, a mixture of 4-hexadecyloxy- and 4-stearoxy-2,2,6,6-tetramethylpiperidine, a condensation product of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, a condensation product of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine as well as 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [136504-96-6]); N-(2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimid, N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimid, 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4.5]decane, a reaction product of 7,7,9,9-tetramethyl-2-cyclo-undecyl-1-oxa-3,8-diaza-4-oxospiro[4.5]decane und epichlorohydrin.

2.7. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-



ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide and mixtures of ortho- and para-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-tridecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxy-propyloxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[4-(dodecyloxy/tridecyloxy-2-hydroxypropoxy)-2-hydroxy-phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-hexyloxy)phenyl-4,6-diphenyl-1,3,5-triazine, 2-(2-hydroxy-4-methoxyphenyl)-4,6-diphenyl-1,3,5-triazine, 2,4,6-tris[2-hydroxy-4-(3-butoxy-2-hydroxy-propoxy)phenyl]-1,3,5-triazine, 2-(2-hydroxyphenyl)-4-(4-methoxyphenyl)-6-phenyl-1,3,5-triazine.

3. Metal deactivators, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloyl hydrazine, N,N'-bis(salicyloyl) hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenyl-propionyl) hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalyl dihydrazide, oxanilide, isophthaloyl dihydrazide, sebacoyl bisphenylhydrazide, N,N'-diacetyl adipoyl dihydrazide, N,N'-bis(salicyloyl)oxalyl dihydrazide, N,N'-bis(salicyloyl)-thiopropionyl dihydrazide.

4. Phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl)-pentaerythritol diphosphite, diisodecyl oxypentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl)pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosphonite, 6-isooctyloxy-2,4,8,10-tetra-tert-butyl-12H-dibenz[d,g]-1,3,2-dioxaphosphocin, 6-fluoro-2,4,8,10-

tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl)methylphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethylphosphite.

5. Hydroxylamines, for example, N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-dioctylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

6. Nitrones, for example, N-benzyl-alpha-phenyl-nitron, N-ethyl-alpha-methyl-nitron, N-octyl-alpha-heptyl-nitron, N-lauryl-alpha-undecyl-nitron, N-tetradecyl-alpha-tridecyl-nitron, N-hexadecyl-alpha-pentadecyl-nitron, N-octadecyl-alpha-heptadecyl-nitron, N-hexadecyl-alpha-heptadecyl-nitron, N-octadecyl-alpha-pentadecyl-nitron, N-heptadecyl-alpha-heptadecyl-nitron, N-octadecyl-alpha-hexadecyl-nitron, nitron derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

7. Thiosynergists, for example, dilauryl thiodipropionate or distearyl thiodipropionate.

8. Peroxide scavengers, for example esters of  $\beta$ -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis( $\beta$ -dodecylmercapto)propionate.

9. Polyamide stabilisers, for example, copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

10. Basic co-stabilisers, for example, melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or tin pyrocatecholate.

11. Nucleating agents, for example, inorganic substances such as talcum, metal oxides such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulfates of, preferably, alkaline earth metals; organic compounds such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds such as ionic copolymers

("ionomers").

12. Fillers and reinforcing agents, for example, calcium carbonate, silicates, glass fibres, glass bulbs, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite, wood flour and flours or fibers of other natural products, synthetic fibers.

13. Other additives, for example, plasticisers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow-control agents, optical brighteners, flameproofing agents, antistatic agents and blowing agents.

14. Benzofuranones and indolinones, for example those disclosed in US-A-4 325 863, US-A-4 338 244, US-A-5 175 312, US-A-5 216 052, US-A-5 252 643, DE-A-4 316 611, DE-A-4 316 622, DE-A-4 316 876, EP-A-0 589 839 or EP-A-0 591 102 or 3-[4-(2-acetoxyethoxy)phenyl]-5,7-di-tert-butyl-benzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butyl-benzofuran-2-one.

The weight ratio of novel stabilizer mixture to the conventional additives can for example be from 1:0.5 to 1:5.


The invention furthermore relates to the use of the novel stabilizer mixture for stabilizing organic material against oxidative, thermal or light-induced degradation.

The organic materials stabilized by means of the novel stabilizer system are distinguished not only by significantly improved light stability but also, in some cases, by improved thermal stability.

The compounds of the formulae IX-1-g-1, XI-1, XII-1, XIII-1 and XIV-1 and the product defined as component I-f) are novel and are likewise a subject of the present invention.

The present invention also relates to:

1) Compounds of the formula D



in which

$\text{R}_{11}$  and  $\text{R}_{13}$  independently of one another are hydrogen,  $\text{C}_1$ - $\text{C}_{12}$ alkyl,  $\text{C}_5$ - $\text{C}_{12}$ cycloalkyl,  $\text{C}_1$ - $\text{C}_4$ alkyl-substituted  $\text{C}_5$ - $\text{C}_{12}$ cycloalkyl, phenyl, -OH- and/or  $\text{C}_1$ - $\text{C}_{10}$ alkyl-substituted phenyl,  $\text{C}_7$ - $\text{C}_9$ phenylalkyl,  $\text{C}_7$ - $\text{C}_9$ phenylalkyl which is substituted on the phenyl radical by -OH and/or  $\text{C}_1$ - $\text{C}_{10}$ alkyl, or are a group of the formula IV-1



in which  $\text{R}_{10}$  is hydrogen,  $\text{C}_1$ - $\text{C}_{18}$ alkyl,  $\text{C}_5$ - $\text{C}_{12}$ cycloalkyl or  $\text{C}_1$ - $\text{C}_4$ alkyl-substituted  $\text{C}_5$ - $\text{C}_{12}$ cycloalkyl,

$\text{R}_{12}$  is  $\text{C}_2$ - $\text{C}_{18}$ alkylene,  $\text{C}_5$ - $\text{C}_7$ cycloalkylene or  $\text{C}_1$ - $\text{C}_4$ alkylenedi( $\text{C}_5$ - $\text{C}_7$ cycloalkylene), or the radicals  $\text{R}_{11}$ ,  $\text{R}_{12}$  and  $\text{R}_{13}$ , together with the nitrogen atoms to which they are attached, form a 5- to 10-membered heterocyclic ring,

the radicals  $\text{R}_{14}$  and  $\text{R}_{15}$ , together with the nitrogen atom to which they are attached, form a 5- to 10-membered heterocyclic ring or a group -NH( $\text{C}_5$ - $\text{C}_{12}$ cycloalkyl),

$n_2$  is a number from 2 to 50 and


at least one of the radicals  $\text{R}_{11}$  and  $\text{R}_{13}$  is a group of the formula IV-1.

$\text{R}_{11}$  and  $\text{R}_{13}$  are preferably a group of the formula IV-1.

$\text{R}_{12}$  is preferably  $\text{C}_2$ - $\text{C}_{10}$ alkylene, especially hexamethylene.

The radicals  $\text{R}_{14}$  and  $\text{R}_{15}$ , together with the nitrogen atom to which they are attached, preferably form morpholino or a group -NH(cyclohexyl).

## 2) Compounds of the formula G-1




(G-1)

in which

$R_{22}$  is hydrogen,  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl or  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl,

$R_{24}$  and  $R_{28}$  independently of one another are hydrogen,  $C_1$ - $C_{30}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl or phenyl,

$R_{25}$  is hydrogen,  $C_1$ - $C_{30}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl,  $C_7$ - $C_9$ phenylalkyl or a group of the formula IV-1



(IV-1)


in which  $R_{10}$  is as defined for  $R_{22}$  and

$n_5$  is a number from 1 to 50.

$R_{24}$  and  $R_{28}$  are preferably  $C_1$ - $C_4$ alkyl, especially methyl.

$R_{25}$  is preferably  $C_1$ - $C_{25}$ alkyl.

3) Compounds of the formula G-2




(G-2)

in which

$R_{21}$  and  $R_{26}$  are a group  $-N(Y_1)-CO-Y_2-CO-N(Y_3)-$ ,

$Y_1$  and  $Y_3$  independently of one another are hydrogen,  $C_1-C_8$ alkyl,  $C_5-C_{12}$ cycloalkyl, phenyl,  $C_7-C_9$ phenylalkyl or a group of the formula IV-1



(IV-1)

in which  $R_{10}$  is hydrogen,  $C_1-C_{18}$ alkyl,  $C_5-C_{12}$ cycloalkyl or  $C_1-C_4$ alkyl-substituted  $C_5-C_{12}$ cycloalkyl,

$Y_2$  is a direct bond or  $C_1-C_4$ alkylene,

$R_{22}$  is as defined for  $R_{10}$ ,

$R_{23}$ ,  $R_{24}$ ,  $R_{27}$  and  $R_{28}$  independently of one another are hydrogen,  $C_1-C_{30}$ alkyl,  $C_5-C_{12}$ cycloalkyl or phenyl.

$R_{25}$  is hydrogen,  $C_1-C_{30}$ alkyl,  $C_5-C_{12}$ cycloalkyl, phenyl,  $C_7-C_9$ phenylalkyl or a group of the formula IV-1 and

$n_5$  is a number from 1 to 50.


$Y_1$  and  $Y_3$  are preferably hydrogen.

$R_{25}$  is preferably a group of the formula IV-1.

The explanations and expressions of preference made with regard to the novel stabilizer mixtures, in respect of the variable radicals and the terminal groups, are to be applied correspondingly to the novel compounds.

The examples which follow illustrate the invention in greater detail. All percentages are by weight, unless stated otherwise.

Example A: Preparation of the compound of the formula




A solution of 23.6 g (0.098 mol) of 4-n-butylamino-1-methoxy-2,2,6,6-tetramethylpiperidine in 25 ml of xylene is added dropwise to a solution of 4.09 (0.0217 mol) of cyanuric chloride in 50 ml of xylene and 6.2 g (0.098 mol) of pulverulent KOH. The reaction mixture is heated at reflux for 23 hours. The solids are then removed by filtration and the filtrate is concentrated under reduced pressure. The crude product obtained is purified by crystallization (ethanol) to give 14.3 g (82 % of theory) of the product indicated above as a white powder. The melting point is 151-153°C.

Elemental analysis for C<sub>45</sub>H<sub>87</sub>N<sub>9</sub>O<sub>3</sub>


Calculated: C, 67.4; H, 10.9; N, 15.7

Found: C, 67.4; H, 11.3; N, 15.7

Example B: Preparation of the compound of the formula




0.5 g of MoO<sub>3</sub> is added to a solution of 24.0 g of the compound of the formula




in 200 ml of cyclohexane. The solution is heated at reflux and 20 ml of tert-butyl hydroperoxide (90 %) are added over the course of 15 minutes. After the reaction mixture has been heated at reflux for 12 hours, the catalyst is removed by filtration and a further 0.5 g of MoO<sub>3</sub> is added to the filtrate, followed by 20 ml of 90 % tert-butyl hydroperoxide. After heating at reflux for a further 12 hours, the red colour has disappeared. The reaction mixture is washed with 5 % aqueous Na<sub>2</sub>SO<sub>3</sub> solution until excess hydroperoxide is no longer present. The reaction solution is washed with water and saline solution, dried over MgSO<sub>4</sub> and evaporated. 15 g of the compound indicated above are obtained as a clear viscous resin without crystals. The NMR and MS data agree with the structure indicated.

Example C: Preparation of the compound of the formula






This is prepared in analogy to the process described in Example B, using 31.87 g of the compound of the formula




1.0 g of  $\text{MoO}_3$  and 40 ml of 90 % tert-butyl hydroperoxide in 600 ml of cyclohexane. 22.2 g of the compound indicated above are obtained as a white, vitreous solid. The melting point is  $135^\circ\text{C}$ . The NMR and MS data agree with the structure indicated.

Example D: Preparation of the compound of the formula




This is prepared in analogy to the process described in Example B, using 25.1 g of the compound of the formula




2.0 g of  $\text{MoO}_3$  and 25 ml of 90 % tert-butyl hydroperoxide in 500 ml of cyclohexane. 36.5 g of the compound indicated above are obtained as a pale yellow vitreous solid. The melting point is 105-125°C. The NMR and MS data agree with the structure indicated.

#### Example E:

Preparation is carried out in analogy to the process described in Example B, using 25.8 g of  $^{\circ}\text{UVASORB HA 88}$  [a compound obtainable by reacting a product, obtained by reaction of a polyamine of the formula




with cyanuric chloride, with a compound of the formula




2.0 g of  $\text{MoO}_3$  and 40 ml of 70 % tert-butyl hydroperoxide in 500 ml of cyclohexane. 47.7 g of a corresponding compound are obtained which comprises 1-cyclohexyloxy-2,2,6,6-tetramethylpiperid-4-yl groups instead of 2,2,6,6-tetramethylpiperid-4-yl groups. The compound is a pale yellow resin with some white crystals. The melting point is 135-145°C. Sintering is at 112°C. The NMR and MS data agree with the structure indicated.

Example F: Preparation of the compound of the formula




11.0 g (14.5 mmol based on the repetitive unit) of the compound of the formula




are dissolved in 200 ml of cyclohexane. 0.1 g of  $\text{MoO}_3$  is added and the mixture is heated at reflux. 10 g (77.5 mmol) of a 70 % (% weight/weight) aqueous tert-butyl hydroperoxide solution are added dropwise slowly at  $80^\circ\text{C}$ . the water/tert-butanol mixture which forms during the reaction is removed by azeotropic distillation. The mixture is then heated at reflux for 14 hours, cooled to  $20-30^\circ\text{C}$ , added to carbon powder and filtered. The solution is washed twice with 10 % (% weight/weight) aqueous  $\text{Na}_2\text{SO}_3$  and with water. The organic phase is dried over  $\text{Na}_2\text{SO}_4$ , filtered and evaporated at  $80^\circ\text{C}/24$  mbar. The residue obtained is a white powder and has a melting point of  $104-108^\circ\text{C}$ . Analysis by NMR ( $^1\text{H}$ ,  $^{13}\text{C}$ ) agrees with the structure indicated above.

Example G: Preparation of the compound of the formula




This is prepared in analogy to the process described in Example F. 11 g (10.3 mmol based on the repetitive unit) of the compound of the formula




are reacted with 10 g of a 10 % (% weight/weight) tert-butyl hydroperoxide solution in cyclohexane in the presence of 0.1 g of MoO<sub>3</sub>. Following evaporation, a white solid with a melting point of 135-139°C is obtained. Analysis by NMR (<sup>1</sup>H, <sup>13</sup>C) agrees with the structure indicated above.

Example H: Preparation of the compound of the formula




This is prepared in analogy to the process described in Example F. 19 g (30.8 mmol based on the repetitive unit) of the compound of the formula




are reacted with 6.6 g of a 70 % (% weight/weight) aqueous tert-butyl hydroperoxide solution in cyclohexane in the presence of 0.5 g of MoO<sub>3</sub>. Following evaporation, a yellow solid with a melting point of 80-87°C is obtained. Analysis by NMR (<sup>1</sup>H, <sup>13</sup>C) agrees with the structure indicated above.

Example I: Preparation of the compound of the formula



This is prepared in analogy to the process described in Example F. 30 g (39.2 mmol based on the repetitive unit) of the compound of the formula




are reacted with 15.2 g of a 70 % (% weight/weight) aqueous tert-butyl hydroperoxide solution in cyclohexane in the presence of 0.8 g of  $\text{MoO}_3$ . Following evaporation, a yellow solid with a melting point of  $72-77^\circ\text{C}$  is obtained. Analysis by NMR ( $^1\text{H}$ ,  $^{13}\text{C}$ ) agrees with the structure indicated above.


**The light stabilizers used in Examples 1 to 3:**

(The mean degree of polymerization is indicated in each case.)


**Light stabilizer 1-a-1 (US-A 5 204 473, Example 58):**




**Light stabilizer 1-a-2 (US-A 5 204 473, Example 4):**




Light stabilizer 1-b-1 (US-A 5 204 473, Example 62):




Light stabilizer 1-c-1 (Example A):




Light stabilizer 1-c-2 (US-A 5 204 473, Example 63):



Light stabilizer 1-d-1 (Example D):




Light stabilizer 1-d-2 (Example C):






Light stabilizer 1-d-3 (Example D):




Light stabilizer 1-e-1 (Example B):




Light stabilizer 1-f-1 (Example E):

®UVASORB HA 88 comprising 1-cyclohexyloxy-2,2,6,6-tetramethylpiperid-4-yl groups instead of 2,2,6,6-tetramethylpiperid-4-yl groups.


Light stabilizer 1-g-1 (Example H):




Light stabilizer 1-g-2 (Example G):




Light stabilizer 1-k-1 (Example F):




Light stabilizer 2-a-3:




Light stabilizer 2-a-4:




Light stabilizer 2-b-1:



Light stabilizer 2-d-1:




Light stabilizer 2-d-2:




Light stabilizer 2-d-3:

$$\left[ \text{Si} \begin{array}{c} \text{CH}_3 \\ | \\ \text{---} \text{O} \text{---} \\ | \\ (\text{CH}_2)_3 \\ | \\ \text{O} \\ | \\ \text{N}(\text{CH}_3)_3 \end{array} \right]_n$$
$$\text{H}_2\text{N}-(\text{CH}_2)_3-\text{NH}-(\text{CH}_2)_2-\text{NH}-(\text{CH}_2)_3-\text{NH}_2$$
CC1(C)C(C)(C)C(C)(C)C1N(C)CC

Light stabilizer 2-g-1:




Light stabilizer 2-g-2:




Light stabilizer 2-i-1:

Mixture of the compounds




and




in a ratio of about 4:1.


Light stabilizer 2-k-1:



Light stabilizer 2-k-2:



Light stabilizer 2-m-l:



Example 1: Light stabilization in low-density polyethylene films.

100 parts of low-density (density = 0.918 g/cm<sup>3</sup>) polyethylene powder are homogenized with 0.03 part of octadecyl  $\beta$ -(3,5-di-tert-butyl-4-hydroxyphenyl)propionate and with the proportion of light stabilizers indicated in Table 1 in a Brabender plastograph at 180°C for 10 minutes. The composition thus obtained is removed from the compounder as rapidly as possible and compressed in a press to give a sheet with a thickness of 2-3 mm. A piece of the resultant green pressure moulding is cut out and pressed between two high-gloss hard aluminium foils for 6 minutes at 170°C under 12 tonnes using a laboratory press to give a film with a thickness of 0.2 mm, which is immediately quenched in cold water. Sections each measuring 55x9 mm<sup>2</sup> are punched out of this film and stored under SO<sub>2</sub> gas in a desiccator for 24 hours. The films are then exposed in an SEPAP 12.24. These test specimens are removed from the exposure apparatus at regular intervals and tested for their carbonyl content in an FTIR spectrometer.

A measure for the protective action is the time ( $T_{0.2 \text{ measured}}$ ) needed to reach a carbonyl extinction of 0.2. The results are summarized in Table 1.

The synergistic effect is determined by a comparison of the calculated  $T_{0.2}$  value with the measured  $T_{0.2}$  value. The  $T_{0.2}$  values are calculated on the basis of the additivity law (B. Ranby and J.F. Rabek, Photodegradation, Photo-oxidation and Photostabilization of Polymers, Principles and Applications, a Wiley-Interscience Publication, 1975, pages 418-422) according to the following equation:

$$T_{0.2 \text{ calculated}} = \frac{T_{0.2 \text{ -Stabilizer 1}} + T_{0.2 \text{ -Stabilizer 2}}}{2}$$

There is a synergistic effect for the mixture in question, when  $T_{0.2 \text{ measured}} > T_{0.2 \text{ calculated}}$ .

Table 1: Light stabilization in low-density polyethylene films.



<u>Light stabilizer</u>	<u>T<sub>0.2</sub> measured in hours</u>	<u>T<sub>0.2</sub> calculated in hours</u>
none (control)	55	
0.15 % (1-b-1)	1730	
0.15 % (2-d-1)	615	
0.075 % (1-b-1) and 0.075 % (2-d-1)	1600	1173

Example 2: Light stabilization in polypropylene block copolymer films.

100 parts of polypropylene block copolymer powder are homogenized with 0.05 part of pentaerythrityl tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate], 0.10 part of tris(2,4-di-tert-butylphenyl) phosphite, 0.1 part of Ca stearate and with the light stabilizers indicated in Table 2 in a Brabender plastograph at 200°C for 10 minutes. The composition thus obtained is removed from the compounder as rapidly as possible and compressed in a toggle press to give a sheet with a thickness of 2-3 mm. A piece of the resultant green press-moulding is cut out and pressed between two high-gloss hard aluminium foils for 6 minutes at 260°C using a laboratory hydraulic press to give a film with a thickness of 0.5 mm, which is immediately cooled in a water-cooled press. Sections each measuring 60 mm x 25 mm are then punched out of this 0.5 mm film and are exposed in a WEATHER-OMETER Ci 65 (black panel temperature 63±2°C, no irrigation). These test specimens are removed from the exposure apparatus at regular intervals and tested for their carbonyl content in an IR spectrometer. The increase in the carbonyl extinction on exposure is a measure of the photooxidative degradation of the polymer and is known from experience to be associated with a deterioration in the mechanical properties.

The time (T<sub>0.2 measured</sub>) needed to reach a carbonyl extinction of 0.2 is shown in Table 2.

The synergistic effect is determined by a comparison of the calculated T<sub>0.2</sub> value with the measured T<sub>0.2</sub> value as shown in Example 1.

Table 2: Light stabilization action in polypropylene block copolymer films.

<u>Light stabilizer</u>	<u>T<sub>0.2</sub> measured in hours</u>	<u>T<sub>0.2</sub> calculated in hours</u>
None	120	
0.1 % of compound 2-m-1	1250	
0.1 % of compound 2-d-1	870	
0.1 % of compound 2-b-1	1480	
0.1 % of compound 2-d-2	1290	
0.1 % of compound 2-f-1	1150	
0.1 % of compound 2-i-1	1040	
0.1 % of compound 2-g-1	515	
0.1 % of compound 2-g-2	340	
0.1 % of compound 2-k-2	865	
0.1 % of compound 2-k-1	675	
0.1 % of compound 2-e-1	1730	
0.1 % of compound 2-a-4	1370	
0.1 % of compound 2-a-3	1320	
0.1 % of compound 1-k-1	755	
0.1 % of compound 1-g-2	300	

0.1 % of compound 1-a-1	955	
0.1 % of compound 1-b-1	680	
0.1 % of compound 1-c-2	1210	
0.1 % of compound 1-e-1	1300	
0.1 % of compound 1-d-2	265	
0.1 % of compound 1-d-1	440	
0.1 % of compound 1-f-1	600	
0.05 % of compound 1-e-1 and 0.05 % of compound 2-m-1	1520	1275
0.05 % of compound 1-e-1 and 0.05 % of compound 2-d-1	1740	1085
0.05 % of compound 1-e-1 and 0.05 % of compound 2-b-1	1750	1390
0.05 % of compound 1-e-1 and 0.05 % of compound 2-d-2	1550	1295
0.05 % of compound 1-e-1 and 0.05 % of compound 2-f-1	1710	1225
0.05 % of compound 1-e-1 and 0.05 % of compound 2-i-1	1500	1170
0.05 % of compound 1-e-1 and 0.05 % of compound 2-g-1	1220	907
0.05 % of compound 1-e-1 and 0.05 % of compound 2-g-2	900	820

0.05 % of compound 1-e-1 and 0.05 % of compound 2-k-2	1330	1082
0.05 % of compound 1-e-1 and 0.05 % of compound 2-k-1	1330	987
0.05 % of compound 1-e-1 and 0.05 % of compound 2-e-1	1720	1515
0.05 % of compound 1-e-1 and 0.05 % of compound 2-a-4	1760	1335
0.05 % of compound 1-e-1 and 0.05 % of compound 2-a-3	1810	1310
0.05 % of compound 1-d-1 and 0.05 % of compound 2-m-1	1015	845
0.05 % of compound 1-d-1 and 0.05 % of compound 2-d-1	810	655
0.05 % of compound 1-d-1 and 0.05 % of compound 2-b-1	1095	960
0.05 % of compound 1-d-1 and 0.05 % of compound 2-d-2	960	865
0.05 % of compound 1-d-1 and 0.05 % of compound 2-f-1	875	795
0.05 % of compound 1-d-1 and 0.05 % of compound 2-i-1	915	740
0.05 % of compound 1-d-1 and 0.05 % of compound 2-g-1	625	477

0.05 % of compound 1-d-1 and 0.05 % of compound 2-g-2	467	390
0.05 % of compound 1-d-1 and 0.05 % of compound 2-k-2	730	652
0.05 % of compound 1-d-1 and 0.05 % of compound 2-k-1	635	557
0.05 % of compound 1-d-1 and 0.05 % of compound 2-e-1	1430	1085
0.05 % of compound 1-d-1 and 0.05 % of compound 2-a-4	1020	905
0.05 % of compound 1-d-1 and 0.05 % of compound 2-a-3	980	880
0.05 % of compound 1-c-2 and 0.05 % of compound 2-m-1	1430	1230
0.05 % of compound 1-c-2 and 0.05 % of compound 2-d-1	1320	1040
0.05 % of compound 1-c-2 and 0.05 % of compound 2-b-1	1550	1345
0.05 % of compound 1-c-2 and 0.05 % of compound 2-d-2	1410	1250
0.05 % of compound 1-c-2 and 0.05 % of compound 2-f-1	1460	1180
0.05 % of compound 1-c-2 and 0.05 % of compound 2-i-1	1300	1125
0.05 % of compound 1-c-2 and		

0.05 % of compound 2-g-1	1095	862
0.05 % of compound 1-c-2 and 0.05 % of compound 2-g-2	820	775
0.05 % of compound 1-c-2 and 0.05 % of compound 2-k-2	1125	1037
0.05 % of compound 1-c-2 and 0.05 % of compound 2-k-1	1155	942
0.05 % of compound 1-c-2 and 0.05 % of compound 2-e-1	1900	1470
0.05 % of compound 1-c-2 and 0.05 % of compound 2-a-4	1400	1290
0.05 % of compound 1-c-2 and 0.05 % of compound 2-a-3	1430	1265
0.05 % of compound 1-f-1 and 0.05 % of compound 2-m-1	1220	925
0.05 % of compound 1-f-1 and 0.05 % of compound 2-d-1	985	735
0.05 % of compound 1-f-1 and 0.05 % of compound 2-b-1	1220	1040
0.05 % of compound 1-f-1 and 0.05 % of compound 2-d-2	1020	945
0.05 % of compound 1-f-1 and 0.05 % of compound 2-f-1	1095	875
0.05 % of compound 1-f-1 and 0.05 % of compound 2-i-1	910	820

0.05 % of compound 1-f-1 and 0.05 % of compound 2-k-1	785	637
0.05 % of compound 1-f-1 and 0.05 % of compound 2-e-1	1630	1165
0.05 % of compound 1-f-1 and 0.05 % of compound 2-a-4	1085	985
0.05 % of compound 1-f-1 and 0.05 % of compound 2-a-3	1230	960
0.05 % of compound 1-b-1 and 0.05 % of compound 2-m-1	1400	965
0.05 % of compound 1-b-1 and 0.05 % of compound 2-d-1	905	775
0.05 % of compound 1-b-1 and 0.05 % of compound 2-d-2	1005	985
0.05 % of compound 1-b-1 and 0.05 % of compound 2-k-2	965	772
0.05 % of compound 1-b-1 and 0.05 % of compound 2-k-1	850	677
0.05 % of compound 1-b-1 and 0.05 % of compound 2-e-1	1760	1205
0.05 % of compound 1-b-1 and 0.05 % of compound 2-a-4	1370	1025
0.05 % of compound 1-b-1 and 0.05 % of compound 2-a-3	1440	1000

0.05 % of compound 1-a-1 and 0.05 % of compound 2-d-2	1300	1122
0.05 % of compound 1-a-1 and 0.05 % of compound 2-f-1	1160	1052
0.05 % of compound 1-a-1 and 0.05 % of compound 2-i-1	1180	997
0.05 % of compound 1-a-1 and 0.05 % of compound 2-g-1	860	735
0.05 % of compound 1-a-1 and 0.05 % of compound 2-k-1	870	815
0.05 % of compound 1-a-1 and 0.05 % of compound 2-e-1	1640	1342
0.05 % of compound 1-a-1 and 0.05 % of compound 2-a-4	1250	1162
0.05 % of compound 1-d-2 and 0.05 % of compound 2-k-2	600	565
0.05 % of compound 1-d-2 and 0.05 % of compound 2-k-1	517	470
0.05 % of compound 1-d-2 and 0.05 % of compound 2-e-1	1190	997
0.05 % of compound 1-d-2 and 0.05 % of compound 2-a-3	875	792
0.05 % of compound 1-k-1 and 0.05 % of compound 2-m-1	1125	1002
0.05 % of compound 1-k-1 and		



0.05 % of compound 2-e-1	1590	1242
0.05 % of compound 1-g-2 and 0.05 % of compound 2-g-1	422	407

Example 3: Light stabilization in low-density polyethylene films.

100 parts of low-density (density =  $0.918 \text{ g/cm}^3$ ) polyethylene powder are homogenized with 0.03 part of octadecyl 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate and with the light stabilizers indicated in Table 3 in a Brabender plastograph at  $180^\circ\text{C}$  for 10 minutes. The composition thus obtained is removed from the compounder as rapidly as possible and compressed in a press to give a sheet with a thickness of 2-3 mm. A piece of the resultant green press-moulding is cut out and pressed between two high-gloss hard aluminium foils for 6 minutes at  $170^\circ\text{C}$  under using a laboratory hydraulic press to give a film with a thickness of 0.2 mm, which is immediately cooled in a water-cooled press. Sections each measuring 60 mm x 25 mm are then punched out of this 0.2 mm film and exposed to fuming hydrochloric acid for 24 hours. This is regarded as a simulation of the effect of halogen containing compounds such as certain pesticides or flame retardants.

The samples are then exposed in a WEATHER-OMETER Ci 65 (black panel temperature  $63 \pm 2^\circ\text{C}$ , no irrigation). The test specimens are removed from the exposure apparatus at regular intervals and tested for their carbonyl content in an IR spectrometer. The increase in the carbonyl extinction on exposure is a measure of the photooxidative degradation of the polymer and is known from experience to be associated with a deterioration in the mechanical properties.

The time ( $T_{0.2 \text{ measured}}$ ) needed to reach a carbonyl extinction of 0.2 is shown in Table 3.

The synergistic effect is determined by a comparison of the calculated  $T_{0.2}$  value with the measured  $T_{0.2}$  value as shown in Example 1.

Table 3: Light stabilization action in low-density polyethylene films.

<u>Light stabilizer</u>	<u><math>T_{0.2 \text{ measured}}</math> in hours</u>	<u><math>T_{0.2 \text{ calculated}}</math> in hours</u>
-------------------------	---	---

None	215	
0.1 % of compound 1-b-1	2620	
0.1 % of compound 1-a-1	1560	
0.1 % of compound 1-c-2	4680	
0.1 % of compound 1-c-1	6760	
0.1 % of compound 2-m-1	about 215	
0.1 % of compound 2-d-1	2920	
0.1 % of compound 2-b-1	2020	
0.1 % of compound 2-d-2	3060	
0.1 % of compound 2-f-1	2740	
0.1 % of compound 2-i-1	3000	
0.1 % of compound 2-g-1	1520	
0.1 % of compound 2-g-2	740	
0.1 % of compound 2-k-2	1840	
0.1 % of compound 2-k-1	2000	
0.1 % of compound 2-a-4	2400	
0.1 % of compound 2-a-3	2440	
0.05 % of compound 1-b-1 and 0.05 % of compound 2-m-1	1620	1417


0.05 % of compound 1-b-1 and 0.05 % of compound 2-d-1	3220	2770
0.05 % of compound 1-b-1 and 0.05 % of compound 2-d-2	2920	2840
0.05 % of compound 1-b-1 and 0.05 % of compound 2-f-1	3200	2680
0.05 % of compound 1-b-1 and 0.05 % of compound 2-i-1	2900	2810
0.05 % of compound 1-b-1 and 0.05 % of compound 2-g-1	2400	2070
0.05 % of compound 1-b-1 and 0.05 % of compound 2-k-2	2400	2230
0.05 % of compound 1-b-1 and 0.05 % of compound 2-k-1	2640	1810
0.05 % of compound 1-b-1 and 0.05 % of compound 2-a-4	3300	2510
0.05 % of compound 1-b-1 and 0.05 % of compound 2-a-3	3000	2530
0.05 % of compound 1-a-1 and 0.05 % of compound 2-d-2	4160	2310
0.05 % of compound 1-a-1 and 0.05 % of compound 2-f-1	4560	2150
0.05 % of compound 1-a-1 and 0.05 % of compound 2-i-1	2940	2280
0.05 % of compound 1-a-1 and		

0.05 % of compound 2-g-1	1970	1540
0.05 % of compound 1-a-1 and 0.05 % of compound 2-g-2	1360	1150
0.05 % of compound 1-a-1 0.05 % of compound 2-k-2	2820	1700
0.05 % of compound 1-a-1 and 0.05 % of compound 2-k-1	2460	1780
0.05 % of compound 1-a-1 and 0.05 % of compound 2-a-4	3300	1980
0.05 % of compound 1-a-1 and 0.05 % of compound 2-a-3	3760	2000
0.05 % of compound 1-c-2 and 0.05 % of compound 2-d-1	4560	3800
0.05 % of compound 1-c-2 and 0.05 % of compound 2-b-1	4000	3350
0.05 % of compound 1-c-1 and 0.05 % of compound 2-m-1	4680	3487
0.05 % of compound 1-c-1 and 0.05 % of compound 2-b-1	5040	4390

WHAT IS CLAIMED IS:

1. A stabilizer mixture comprising a component I-a), I-b), I-c), I-d), I-e), I-f), I-g), I-h), I-i), I-j), I-k) or I-l) and a component II-a), II-b), II-c), II-d), II-e), II-f), II-g), II-h), II-i), II-j), II-k), II-l) or II-m), where

component I-a) is at least one compound of the formula I-1



in which

$\text{R}_1$  is hydrogen,  $\text{C}_1\text{-C}_{18}$ alkyl,  $\text{C}_5\text{-C}_{12}$ cycloalkyl or  $\text{C}_1\text{-C}_4$ alkyl-substituted  $\text{C}_5\text{-C}_{12}$ cycloalkyl,

$n_1$  is 1, 2 or 4,

if  $n_1$  is 1,  $\text{R}_2$  is  $\text{C}_1\text{-C}_{25}$ alkyl,

if  $n_1$  is 2,  $\text{R}_2$  is  $\text{C}_1\text{-C}_{14}$ alkylene and


if  $n_1$  is 4,  $\text{R}_2$  is  $\text{C}_4\text{-C}_{10}$ alkanetetrayl,

with the provisos that,

(1) in a stabilizer mixture comprising component I-a) and component II-b) or II-m), if  $n_1=2$ ,  $\text{R}_1$  is other than  $\text{C}_1\text{-C}_{18}$ alkyl and

(2) in a stabilizer mixture comprising component I-a) and component II-d), if  $n_1=2$  and  $\text{R}_1=\text{C}_1\text{-C}_{18}$ alkyl, the group  $-\text{N}(\text{A}_{14})\text{A}_{15}$  is a 5- to 10-membered heterocyclic ring;


component I-b) is at least one compound of the formula II-1



in which

$\text{R}_3$  and  $\text{R}_7$  independently of one another are hydrogen or  $\text{C}_1\text{-C}_{12}$ alkyl,

$R_4$ ,  $R_5$  and  $R_6$  independently of one another are  $C_2$ - $C_{10}$ alkylene and  $X_1$ ,  $X_2$ ,  $X_3$ ,  $X_4$ ,  $X_5$ ,  $X_6$ ,  $X_7$  and  $X_8$  independently of one another are a group of the formula III-1



in which

$R_8$  is hydrogen,  $C_1$ - $C_{12}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl,  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl, phenyl, -OH- and/or  $C_1$ - $C_{10}$ alkyl-substituted phenyl,  $C_7$ - $C_9$ phenylalkyl,  $C_7$ - $C_9$ phenylalkyl which is substituted on the phenyl radical by -OH and/or  $C_1$ - $C_{10}$ alkyl, or is a group of the formula IV-1



and  $R_9$  and  $R_{10}$  independently of one another are as defined for  $R_1$ ;


component I-c) is at least one compound of the formula V-1



in which

$X_9$ ,  $X_{10}$  and  $X_{11}$  independently of one another are a group of the formula III-1;

component I-d) is at least one compound of the formula VI-1




in which

$R_{11}$ ,  $R_{13}$ ,  $R_{14}$  and  $R_{15}$  independently of one another are hydrogen,  $C_1$ - $C_{12}$ alkyl.

C<sub>5</sub>-C<sub>12</sub>cycloalkyl, C<sub>1</sub>-C<sub>4</sub>alkyl-substituted C<sub>5</sub>-C<sub>12</sub>cycloalkyl, phenyl, -OH- and/or C<sub>1</sub>-C<sub>10</sub>alkyl-substituted phenyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl which is substituted on the phenyl radical by -OH and/or C<sub>1</sub>-C<sub>10</sub>alkyl, or are a group of the formula IV-1, R<sub>12</sub> is C<sub>2</sub>-C<sub>18</sub>alkylene, C<sub>5</sub>-C<sub>7</sub>cycloalkylene or C<sub>1</sub>-C<sub>4</sub>alkylenedi(C<sub>5</sub>-C<sub>7</sub>cycloalkylene), or the radicals R<sub>11</sub>, R<sub>12</sub> and R<sub>13</sub>, together with the nitrogen atoms to which they are attached, form a 5- to 10-membered heterocyclic ring, or R<sub>14</sub> and R<sub>15</sub>, together with the nitrogen atom to which they are attached, form a 5- to 10-membered heterocyclic ring, n<sub>2</sub> is a number from 2 to 50 and at least one of the radicals R<sub>11</sub>, R<sub>13</sub>, R<sub>14</sub> and R<sub>15</sub> is a group of the formula IV-1;

component I-e) is at least one compound of the formula VII-1





in which

R<sub>16</sub> is C<sub>1</sub>-C<sub>10</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>cycloalkyl, C<sub>1</sub>-C<sub>4</sub>alkyl-substituted C<sub>5</sub>-C<sub>12</sub>cycloalkyl, phenyl or C<sub>1</sub>-C<sub>10</sub>alkyl-substituted phenyl,  
R<sub>17</sub> is C<sub>3</sub>-C<sub>10</sub>alkylene,  
R<sub>18</sub> is as defined for R<sub>1</sub> and  
n<sub>3</sub> is a number from 1 to 50;

component I-f) is a product obtainable by

a) reacting a product, obtained by reaction of a polyamine of the formula VIII-1-a with cyanuric chloride, with a compound of the formula VIII-1-b






(VIII-1-b)

in which

$n_4'$ ,  $n_4''$  and  $n_4'''$  independently of one another are a number from 2 to 12 and

$R_{19}$  is hydrogen,  $C_1$ - $C_{12}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl or  $C_7$ - $C_9$ phenylalkyl, and


b) further reacting the 2,2,6,6-tetramethylpiperid-4-yl groups present in the molecule to give groups of the formula VIII-1-c



(VIII-1-c)

in which  $R_{20}$  is as defined for  $R_1$ ;

component I-g) is at least one compound of the formula IX-1



(IX-1)

in which

$R_{21}$  and  $R_{26}$  independently of one another are a direct bond or a group

$-N(Y_1)-CO-Y_2-CO-N(Y_3)-$ ,

$Y_1$  and  $Y_3$  independently of one another are hydrogen,  $C_1$ - $C_8$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl,



phenyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl or a group of the formula IV-1,

Y<sub>2</sub> is a direct bond or C<sub>1</sub>-C<sub>4</sub>alkylene,

R<sub>22</sub> is as defined for R<sub>1</sub>,


R<sub>23</sub>, R<sub>24</sub>, R<sub>27</sub> and R<sub>28</sub> independently of one another are hydrogen, C<sub>1</sub>-C<sub>30</sub>alkyl,

C<sub>5</sub>-C<sub>12</sub>cycloalkyl or phenyl,

R<sub>25</sub> is hydrogen, C<sub>1</sub>-C<sub>30</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>cycloalkyl, phenyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl or a group of the formula IV-1 and

n<sub>5</sub> is a number from 1 to 50;

component I-h) is at least one compound of the formula X-1




in which

R<sub>29</sub> is C<sub>1</sub>-C<sub>24</sub>alkyl and

R<sub>30</sub> is as defined for R<sub>1</sub>;

component I-i) is at least one compound of the formula XI-1



in which

R<sub>31</sub> is as defined for R<sub>1</sub> and

n<sub>6</sub> is a number from 2 to 50;

component I-j) is at least one compound of the formula XII-1



in which

R<sub>32</sub> and R<sub>33</sub> together are C<sub>2</sub>-C<sub>14</sub>alkylene,


R<sub>34</sub> is hydrogen or a group -Z<sub>1</sub>-COO-Z<sub>2</sub>,

Z<sub>1</sub> is C<sub>2</sub>-C<sub>14</sub>alkylene and

Z<sub>2</sub> is C<sub>1</sub>-C<sub>24</sub>alkyl and

R<sub>35</sub> is as defined for R<sub>1</sub>;

component I-k) is at least one compound of the formula XIII-1



in which R<sub>36</sub>, R<sub>37</sub>, R<sub>38</sub>, R<sub>39</sub> and R<sub>40</sub> independently of one another are a direct bond or C<sub>1</sub>-C<sub>10</sub>alkylene,

R<sub>41</sub> is as defined for R<sub>1</sub> and

n<sub>7</sub> is a number from 1 to 50;

component I-l) is at least one compound of the formula XIV-1

$$\text{---CH}_2\text{---CH---CH}_2\text{---A}$$

|  
OH

$$\left[ \begin{array}{c} \text{H}_3\text{C} \quad \text{CH}_3 \\ | \quad / \\ \text{A}_1 - \text{N} \quad \text{C} \\ | \quad \backslash \\ \text{H}_3\text{C} \quad \text{CH}_3 \end{array} \text{---} \text{O} \text{---} \text{C} \begin{array}{c} \text{O} \\ || \end{array} \text{---} \right]_{b_1} \text{---} \text{A}_2$$


The structure shows a 1,3,5-triazine ring with substituents T<sub>1</sub>, T<sub>2</sub>, and T<sub>7</sub> at the 2, 4, and 6 positions respectively. The nitrogen at position 1 is connected to a linker A<sub>3</sub>. The nitrogen at position 3 is connected to a linker A<sub>4</sub>, which is further connected to a nitrogen atom. This nitrogen is connected to a linker A<sub>5</sub>, which is further connected to another nitrogen atom. This nitrogen is connected to a linker A<sub>6</sub>, which is further connected to a nitrogen atom. This nitrogen is connected to a linker A<sub>7</sub>, which is further connected to the nitrogen at position 4 of the triazine ring. The nitrogen at position 5 of the triazine ring is connected to a substituent T<sub>3</sub>. The nitrogen at position 6 of the triazine ring is connected to a substituent T<sub>4</sub>. The nitrogen at position 7 of the triazine ring is connected to a substituent T<sub>5</sub>. The nitrogen at position 8 of the triazine ring is connected to a substituent T<sub>6</sub>.

A<sub>4</sub>, A<sub>5</sub> and A<sub>6</sub> independently of one another are C<sub>2</sub>-C<sub>10</sub>alkylene and

T<sub>1</sub>, T<sub>2</sub>, T<sub>3</sub>, T<sub>4</sub>, T<sub>5</sub>, T<sub>6</sub>, T<sub>7</sub> and T<sub>8</sub> independently of one another are a group of the formula III-2



in which A<sub>8</sub> is hydrogen, C<sub>1</sub>-C<sub>12</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>cycloalkyl, C<sub>1</sub>-C<sub>4</sub>alkyl-substituted C<sub>5</sub>-C<sub>12</sub>cycloalkyl, phenyl, -OH- and/or C<sub>1</sub>-C<sub>10</sub>alkyl-substituted phenyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl which is substituted on the phenyl radical by -OH and/or C<sub>1</sub>-C<sub>10</sub>alkyl, or is a group of the formula IV-2



and A<sub>9</sub> and A<sub>10</sub> independently of one another are as defined for A<sub>1</sub>;


component II-c) is at least one compound of the formula V-2



in which

T<sub>9</sub>, T<sub>10</sub> and T<sub>11</sub> independently of one another are a group of the formula III-2;

component II-d) is at least one compound of the formula VI-2



in which

A<sub>11</sub>, A<sub>13</sub>, A<sub>14</sub> and A<sub>15</sub> independently of one another are hydrogen, C<sub>1</sub>-C<sub>12</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>cycloalkyl, C<sub>1</sub>-C<sub>4</sub>alkyl-substituted C<sub>5</sub>-C<sub>12</sub>cycloalkyl, phenyl, -OH- and/or C<sub>1</sub>-C<sub>10</sub>alkyl-substituted phenyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl, C<sub>7</sub>-C<sub>9</sub>phenylalkyl which is substituted


on the phenyl radical by -OH and/or  $C_1$ - $C_{10}$ alkyl, or are a group of the formula IV-2,  $A_{12}$  is  $C_2$ - $C_{18}$ alkylene,  $C_5$ - $C_7$ cycloalkylene or  $C_1$ - $C_4$ alkylenedi( $C_5$ - $C_7$ cycloalkylene), or the radicals  $A_{11}$ ,  $A_{12}$  and  $A_{13}$ , together with the nitrogen atoms to which they are attached, form a 5- to 10-membered heterocyclic ring, or

$A_{14}$  and  $A_{15}$ , together with the nitrogen atom to which they are attached, form a 5- to 10-membered heterocyclic ring,

$b_2$  is a number from 2 to 50 and

at least one of the radicals  $A_{11}$ ,  $A_{13}$ ,  $A_{14}$  and  $A_{15}$  is a group of the formula IV-2;

component II-e) is at least one compound of the formula VII-2



in which


$A_{16}$  is  $C_1$ - $C_{10}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl,  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl, phenyl or  $C_1$ - $C_{10}$ alkyl-substituted phenyl,


$A_{17}$  is  $C_3$ - $C_{10}$ alkylene,

$A_{18}$  is as defined for  $A_1$  and

$b_3$  is a number from 1 to 50;

component II-f) is a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula VIII-2-a with cyanuric chloride, with a compound of the formula VIII-2-b





(VIII-2-b)


in which

$b_4'$ ,  $b_4''$  and  $b_4'''$  independently of one another are a number from 2 to 12,

$A_{19}$  is hydrogen,  $C_1$ - $C_{12}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl or  $C_7$ - $C_9$ phenylalkyl and

$A_{20}$  is as defined for  $A_1$ ;

component II-g) is at least one compound of the formula IX-2



(IX-2)

in which

$A_{21}$  and  $A_{26}$  independently of one another are a direct bond or a group

$-N(E_1)-CO-E_2-CO-N(E_3)-$ ,

$E_1$  and  $E_3$  independently of one another are hydrogen,  $C_1$ - $C_8$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl,  $C_7$ - $C_9$ phenylalkyl or a group of the formula IV-2,

$E_2$  is a direct bond or  $C_1$ - $C_4$ alkylene,

$A_{22}$  is as defined for  $A_1$ ,


$A_{23}$ ,  $A_{24}$ ,  $A_{27}$  and  $A_{28}$  independently of one another are hydrogen,  $C_1$ - $C_{30}$ alkyl,

$C_5$ - $C_{12}$ cycloalkyl or phenyl,

$A_{25}$  is hydrogen,  $C_1$ - $C_{30}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl,  $C_7$ - $C_9$ phenylalkyl or a group of


the formula IV-2 and  
 $b_5$  is a number from 1 to 50;

component II-h) is at least one compound of the formula X-2




in which  
 $A_{29}$  is  $C_1$ - $C_{24}$ alkyl and  
 $A_{30}$  is as defined for  $A_1$ ;

component II-i) is at least one compound of the formula XI-2



in which  
 $A_{31}$  is as defined for  $A_1$  and  
 $b_6$  is a number from 2 to 50;

component II-j) is at least one compound of the formula XII-2



in which

$A_{32}$  and  $A_{33}$  together form  $C_2-C_{14}$ alkylene,


$A_{34}$  is hydrogen or a group  $-G_1-COO-G_2$ ,

$G_1$  is  $C_2-C_{14}$ alkylene and

$G_2$  is  $C_1-C_{24}$ alkyl and

$A_{35}$  is as defined for  $A_1$ ;

component II-k) is at least one compound of the formula XIII-2




in which  $A_{36}$ ,  $A_{37}$ ,  $A_{38}$ ,  $A_{39}$  and  $A_{40}$  independently of one another are a direct bond or  $C_1-C_{10}$ alkylene,

$A_{41}$  is as defined for  $A_1$  and


$b_7$  is a number from 1 to 50;

component II-l) is at least one compound of the formula XIV-2



in which


$T_{12}$ ,  $T_{13}$  and  $T_{14}$  independently of one another are a group of the formula XV-2



in which L is a group of the formula III-2;



component II-m) is at least one compound of the formula XVI-2



in which  $\text{A}_{42}$  is hydrogen or methyl,

$\text{A}_{43}$  is a direct bond or  $\text{C}_1\text{-C}_{10}$ alkylene and

$b_8$  is a number from 2 to 50.

2. A stabilizer mixture according to claim 1, in which  $\text{R}_1$ ,  $\text{R}_9$ ,  $\text{R}_{10}$ ,  $\text{R}_{18}$ ,  $\text{R}_{20}$ ,  $\text{R}_{22}$ ,  $\text{R}_{30}$ ,  $\text{R}_{31}$ ,  $\text{R}_{35}$  and  $\text{R}_{41}$  independently of one another are  $\text{C}_1\text{-C}_{12}$ alkyl,  $\text{C}_5\text{-C}_8$ cycloalkyl or methyl-substituted  $\text{C}_5\text{-C}_8$ cycloalkyl.
3. A stabilizer mixture according to claim 1, in which  $\text{R}_1$ ,  $\text{R}_9$ ,  $\text{R}_{10}$ ,  $\text{R}_{18}$ ,  $\text{R}_{20}$ ,  $\text{R}_{22}$ ,  $\text{R}_{30}$ ,  $\text{R}_{31}$ ,  $\text{R}_{35}$  and  $\text{R}_{41}$  independently of one another are methyl, octyl or cyclohexyl.
4. A stabilizer mixture according to claim 1, in which  $\text{A}_1$ ,  $\text{A}_9$ ,  $\text{A}_{10}$ ,  $\text{A}_{18}$ ,  $\text{A}_{20}$ ,  $\text{A}_{22}$ ,  $\text{A}_{30}$ ,  $\text{A}_{31}$ ,  $\text{A}_{35}$  and  $\text{A}_{41}$  independently of one another are hydrogen or methyl.
5. A stabilizer mixture according to claim 1, comprising a component I-a), I-b), I-c), I-d), I-e), I-f), I-g), I-h), I-i), I-j), I-k) or I-l) and a component II-a), II-b), II-d), II-e), II-f), II-g), II-i), II-k) or II-m).
6. A stabilizer mixture according to claim 1, comprising a component I-a) and a component II-b), II-d) or II-m).
7. A stabilizer mixture according to claim 1, comprising a component I-b) and a component II-b), II-d) or II-m).
8. A stabilizer mixture according to claim 1, comprising a component I-c) and a component II-b), II-d) or II-m).
9. A stabilizer mixture according to claim 1,  
in which  $n_1$  is 1, 2 or 4,  
if  $n_1$  is 1,  $\text{R}_2$  is  $\text{C}_{10}\text{-C}_{20}$ alkyl.

if  $n_1$  is 2,  $R_2$  is  $C_6-C_{10}$ alkylene and  
if  $n_1$  is 4,  $R_2$  is butanetetrayl;

$R_3$  and  $R_7$  independently of one another are hydrogen or  $C_1-C_4$ alkyl,  
 $R_4$ ,  $R_5$  and  $R_6$  independently of one another are  $C_2-C_6$ alkylene,  
 $R_8$  is hydrogen,  $C_1-C_6$ alkyl,  $C_5-C_8$ cycloalkyl, methyl-substituted  $C_5-C_8$ cycloalkyl,  
phenyl,  $C_7-C_9$ phenylalkyl or a group of the formula IV-1;

$R_{11}$ ,  $R_{13}$ ,  $R_{14}$  and  $R_{15}$  independently of one another are hydrogen,  $C_1-C_8$ alkyl,  
 $C_5-C_8$ cycloalkyl, methyl-substituted  $C_5-C_8$ cycloalkyl, phenyl,  $C_7-C_9$ phenylalkyl or a  
group of the formula IV-1, or  
the radicals  $R_{14}$  and  $R_{15}$ , together with the nitrogen atom to which they are attached, form  
a 6-membered heterocyclic ring,  
 $R_{12}$  is  $C_2-C_{10}$ alkylene and  
 $n_2$  is a number from 2 to 25;

$R_{16}$  is  $C_1-C_4$ alkyl,  $C_5-C_8$ cycloalkyl or phenyl,  
 $R_{17}$  is  $C_3-C_6$ alkylene and  
 $n_3$  is a number from 1 to 25;

$n_4'$ ,  $n_4''$  and  $n_4'''$  independently of one another are a number from 2 to 4 and  
 $R_{19}$  is  $C_1-C_4$ alkyl;

$R_{21}$  and  $R_{26}$  independently of one another are a direct bond or a group  
- $N(Y_1)$ -CO- $Y_2$ -CO- $N(Y_3)$ -,  
 $Y_1$  and  $Y_3$  independently of one another are hydrogen or  $C_1-C_4$ alkyl,  
 $Y_2$  is a direct bond,  
 $R_{23}$  and  $R_{27}$  are  $C_1-C_{25}$ alkyl or phenyl,  
 $R_{24}$  and  $R_{28}$  are hydrogen or  $C_1-C_4$ alkyl,  
 $R_{25}$  is  $C_1-C_{25}$ alkyl or a group of the formula IV-1 and  
 $n_5$  is a number from 1 to 25;

$R_{29}$  is  $C_8-C_{15}$ alkyl;

$n_6$  is a number from 2 to 25;

$R_{32}$  and  $R_{33}$  together form  $C_8-C_{14}$ alkylene,

$R_{34}$  is hydrogen or a group  $-Z_1-COO-Z_2$ ,

$Z_1$  is  $C_2-C_6$ alkylene and




$Z_2$  is  $C_8-C_{15}$ alkyl;

$R_{36}$ ,  $R_{38}$ ,  $R_{39}$  and  $R_{40}$  independently of one another are  $C_1-C_4$ alkylene,

$R_{37}$  is a direct bond and


$n_7$  is a number from 1 to 25.

10. A stabilizer mixture according to claim 1, in which component I-a) is at least one compound of the formula I-1-a-1, I-1-a-2 or I-1-a-3



in which  $R_1$  is methyl, octyl or cyclohexyl;


component I-b) is at least one compound of the formula II-1-b



(II-1-b)

in which  $R_9$  is as defined for  $R_1$ ;




component I-c) is at least one compound of the formula V-1-c



(V-1-c)


in which  $R_9$  is as defined above;

component I-d) is at least one compound of the formula VI-1-d-1, VI-1-d-2 or VI-1-d-3



in which  $R_{10}$  is as defined for  $R_1$  and  $n_2$  is a number from 2 to 25;


component I-e) is at least one compound of the formula VII-1-e




in which  $\text{R}_{18}$  is as defined for  $\text{R}_1$  and  $n_3$  is a number from 1 to 25;

component I-f) is a product obtainable by

a) reacting a product, obtained by reaction of a polyamine of the formula






with cyanuric chloride, with a compound of the formula



b) further reacting the 2,2,6,6-tetramethylpiperid-4-yl groups which are present in the molecule to give groups of the formula VIII-1-c;


component I-g) is at least one compound of the formula IX-1-g-1, IX-1-g-2 or IX-1-g-3





in which  $R_{10}$  and  $R_{22}$  are as defined for  $R_1$  and  $n_5$  is a number from 1 to 25;

component 1-h) is at least one compound of the formula X-1-h





in which  $R_{30}$  is as defined for  $R_1$ ;

component 1-i) is at least one compound of the formula (XI-1) in which  $R_{31}$  is as defined


for  $R_1$  and  $n_6$  is a number from 2 to 25;

component I-j) is at least one compound of the formula XII-1-j-1 or XII-1-j-2



in which  $R_{35}$  is as defined for  $R_1$ ;


component I-k) is at least one compound of the formula XIII-1-k



in which  $R_{41}$  is as defined for  $R_1$  and  $n_7$  is a number from 1 to 25;

component I-l) is at least one compound of the formula XIV-1-l





in which  $R_9$  is as defined for  $R_1$ .

11. Stabilizer mixture according to claim 1,

in which  $b_1$  is 1, 2 or 4,

if  $b_1$  is 1,  $A_2$  is  $C_{10}$ - $C_{20}$ alkyl,

if  $b_1$  is 2,  $A_2$  is  $C_6$ - $C_{10}$ alkylene and

if  $b_1$  is 4,  $A_2$  is butanetetrayl;

$A_3$  and  $A_7$  independently of one another are hydrogen or  $C_1$ - $C_4$ alkyl,

$A_4$ ,  $A_5$  and  $A_6$  independently of one another are  $C_2$ - $C_6$ alkylene,

$A_8$  is hydrogen,  $C_1$ - $C_6$ alkyl,  $C_5$ - $C_8$ cycloalkyl, methyl-substituted  $C_5$ - $C_8$ cycloalkyl, phenyl,  $C_7$ - $C_9$ phenylalkyl or a group of the formula IV-2;

$A_{11}$ ,  $A_{13}$ ,  $A_{14}$  and  $A_{15}$  independently of one another are hydrogen,  $C_1$ - $C_8$ alkyl,  $C_5$ - $C_8$ cycloalkyl, methyl-substituted  $C_5$ - $C_8$ cycloalkyl, phenyl,  $C_7$ - $C_9$ phenylalkyl or a group of the formula IV-2, or

the radicals  $A_{14}$  and  $A_{15}$ , together with the nitrogen atom to which they are attached, form a 6-membered heterocyclic ring,

$A_{12}$  is  $C_2$ - $C_{10}$ alkylene and

$b_2$  is a number from 2 to 25;

$A_{16}$  is  $C_1$ - $C_4$ alkyl,  $C_5$ - $C_8$ cycloalkyl or phenyl,

$A_{17}$  is  $C_3$ - $C_6$ alkylene and

$b_3$  is a number from 1 to 25;

$b_4'$ ,  $b_4''$  and  $b_4'''$  independently of one another are a number from 2 to 4 and

$A_{19}$  is  $C_1$ - $C_4$ alkyl;

$A_{21}$  and  $A_{26}$  independently of one another are a direct bond or a group

$-N(E_1)-CO-E_2-CO-N(E_3)-$ ,

$E_1$  and  $E_3$  independently of one another are hydrogen or  $C_1-C_4$ alkyl,

$E_2$  is a direct bond,

$A_{23}$  and  $A_{27}$  are  $C_1-C_{25}$ alkyl or phenyl,

$A_{24}$  and  $A_{28}$  are hydrogen or  $C_1-C_4$ alkyl,

$A_{25}$  is  $C_1-C_{25}$ alkyl or a group of the formula IV-2 and

$b_5$  is a number from 1 to 25;

$A_{29}$  is  $C_8-C_{15}$ alkyl;

$b_6$  is a number from 2 to 25;

$A_{32}$  and  $A_{33}$  together form  $C_8-C_{14}$ alkylene,

$A_{34}$  is hydrogen or a group  $-G_1-COO-G_2$ ,

$G_1$  is  $C_2-C_6$ alkylene and

$G_2$  is  $C_8-C_{15}$ alkyl;


$A_{36}$ ,  $A_{38}$ ,  $A_{39}$  and  $A_{40}$  independently of one another are  $C_1-C_4$ alkylene,

$A_{37}$  is a direct bond and

$b_7$  is a number from 1 to 25.


12. A stabilizer mixture according to claim 1, in which

component II-a) is at least one compound of the formula I-2-a-3



in which  $A_1$  is hydrogen or methyl;


component II-b) is at least one compound of the formula II-2-b




(II-2-b)

in which  $A_9$  is as defined for  $A_1$ ;


component II-d) is at least one compound of the formula VI-2-d-1, VI-2-d-2 or VI-2-d-3



(VI-2-d-1)




(VI-2-d-2)



(VI-2-d-3)


in which  $A_{10}$  is as defined for  $A_1$  and  $b_2$  is a number from 2 to 25;

component II-e) is at least one compound of the formula VI-2-e




in which  $A_{18}$  is as defined for  $A_1$  and  $b_3$  is a number from 1 to 25;

component II-f) is a product obtainable by reacting a product, obtained by reaction of a polyamine of the formula






with cyanuric chloride, with a compound of the formula



in which  $A_{20}$  is as defined for  $A_1$ ;


component II-g) is at least one compound of the formula LX-2-g-1, IX-2-g-2 or IX-2-g-3



in which  $A_{10}$  and  $A_{22}$  are as defined for  $A_1$  and  $b_5$  is a number from 1 to 25;


component II-i) is at least one compound of the formula XI-2 in which  $A_{31}$  is as defined for  $A_1$  and  $b_6$  is a number from 2 to 25;

component II-k) is at least one compound of the formula XIII-2-k




in which  $A_{41}$  is as defined for  $A_1$  and  $b_7$  is a number from 1 to 25;

component II-m) is at least one compound of the formula XVI-2-m




in which  $b_8$  is a number from 2 to 25.

13. A composition comprising an organic material sensitive to oxidative, thermal or light-induced degradation and a stabilizer mixture according to claim 1.
14. A composition according to claim 13, in which the organic material is a polyolefin.
15. A composition according to claim 13, in which the organic material is polyethylene, polypropylene or a copolymer of polyethylene or polypropylene.
16. A method of stabilizing an organic material sensitive to oxidative, thermal or light-induced degradation, which comprises incorporating into the organic material a stabilizer mixture according to claim 1.
17. A compound of the formula IX-1-g-1



in which  $R_{10}$  and  $R_{22}$  independently of one another are hydrogen,  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl or  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl and  $n_5$  is a number from 1 to 25.


18. A compound of the formula XI-1



in which

$R_{31}$  is hydrogen,  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl or  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl and  $n_6$  is a number from 2 to 50.

19. A compound of the formula XII-1



(XII-1)

in which

$R_{32}$  and  $R_{33}$  together form  $C_2$ - $C_{14}$ alkylene,


$R_{34}$  is hydrogen or a group  $-Z_1-COO-Z_2$ ,

$Z_1$  is  $C_2$ - $C_{14}$ alkylene and

$Z_2$  is  $C_1$ - $C_{24}$ alkyl and

$R_{35}$  is hydrogen,  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl or  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl.

20. A compound of the formula XIII-1



(XIII-1)


in which  $R_{36}$ ,  $R_{37}$ ,  $R_{38}$ ,  $R_{39}$  and  $R_{40}$  independently of one another are a direct bond or  $C_1$ - $C_{10}$ alkylene,

$R_{41}$  is hydrogen,  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl or  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl and

$n_7$  is a number from 1 to 50.

21. A compound of the formula XIV-1







(XIV-1)

in which

$X_{12}$ ,  $X_{13}$  and  $X_{14}$  independently of one another are a group of the formula XV-1




in which A is a group of the formula III-1



(III-1)

in which  $R_8$  is hydrogen,  $C_1$ - $C_{12}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl,  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl, phenyl, -OH- and/or  $C_1$ - $C_{10}$ alkyl-substituted phenyl,  $C_7$ - $C_9$ phenylalkyl,  $C_7$ - $C_9$ phenylalkyl which is substituted on the phenyl radical by -OH and/or  $C_1$ - $C_{10}$ alkyl, or is a group of the formula IV-1




(IV-1)

and  $R_9$  and  $R_{10}$  independently of one another are hydrogen,  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl or  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl.

22. A product obtainable by

a) reacting a product, obtained by reaction of a polyamine of the formula VIII-1-a with cyanuric chloride, with a compound of the formula VIII-1-b



(VIII-1-a)



in which

$n_4'$ ,  $n_4''$  and  $n_4'''$  independently of one another are a number from 2 to 12 and


$R_{19}$  is hydrogen,  $C_1$ - $C_{12}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl, phenyl or  $C_7$ - $C_9$ phenylalkyl, and

b) further reacting the 2,2,6,6-tetramethylpiperid-4-yl groups present in the molecule to give groups of the formula VIII-1-c



in which  $R_{20}$  is hydrogen,  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl or  $C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl.

23. A compound of the formula D



in which

$R_{11}$  and  $R_{13}$  independently of one another are hydrogen,  $C_1$ - $C_{12}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl,

$C_1$ - $C_4$ alkyl-substituted  $C_5$ - $C_{12}$ cycloalkyl, phenyl, -OH- and/or  $C_1$ - $C_{10}$ alkyl-substituted

phenyl,  $C_7$ - $C_9$ phenylalkyl,  $C_7$ - $C_9$ phenylalkyl which is substituted on the phenyl radical by

-OH and/or  $C_1$ - $C_{10}$ alkyl, or are a group of the formula IV-1



in which  $R_{10}$  is hydrogen,  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ cycloalkyl or  $C_1$ - $C_4$ alkyl-substituted

$C_5$ - $C_{12}$ cycloalkyl,

$R_{12}$  is  $C_2$ - $C_{18}$ alkylene,  $C_5$ - $C_7$ cycloalkylene or  $C_1$ - $C_4$ alkylenedi( $C_5$ - $C_7$ cycloalkylene), or


the radicals  $R_{11}$ ,  $R_{12}$  and  $R_{13}$ , together with the nitrogen atoms to which they are attached, form a 5- to 10-membered heterocyclic ring,

the radicals  $R_{14}$  and  $R_{15}$ , together with the nitrogen atom to which they are attached, form a 5- to 10-membered heterocyclic ring or a group  $-NH(C_5-C_{12}\text{cycloalkyl})$ ,

$n_2$  is a number from 2 to 50 and

at least one of the radicals  $R_{11}$  and  $R_{13}$  is a group of the formula IV-1.

24. A compound of the formula G-1




(G-1)

in which

$R_{22}$  is hydrogen,  $C_1-C_{18}$ alkyl,  $C_5-C_{12}$ cycloalkyl or  $C_1-C_4$ alkyl-substituted  $C_5-C_{12}$ cycloalkyl,

$R_{24}$  and  $R_{28}$  independently of one another are hydrogen,  $C_1-C_{30}$ alkyl,  $C_5-C_{12}$ cycloalkyl or phenyl,

$R_{25}$  is hydrogen,  $C_1-C_{30}$ alkyl,  $C_5-C_{12}$ cycloalkyl, phenyl,  $C_7-C_9$ phenylalkyl or a group of the formula IV-1




(IV-1)

in which  $R_{10}$  is as defined for  $R_{22}$  and

$n_5$  is a number from 1 to 50.

25. A compound of the formula G-2




(G-2)

in which

$R_{21}$  and  $R_{26}$  are a group  $-N(Y_1)-CO-Y_2-CO-N(Y_3)-$ ,

$Y_1$  and  $Y_3$  independently of one another are hydrogen,  $C_1-C_8$ alkyl,  $C_5-C_{12}$ cycloalkyl, phenyl,  $C_7-C_9$ phenylalkyl or a group of the formula IV-1



(IV-1)

in which  $R_{10}$  is hydrogen,  $C_1-C_{18}$ alkyl,  $C_5-C_{12}$ cycloalkyl or  $C_1-C_4$ alkyl-substituted  $C_5-C_{12}$ cycloalkyl,

$Y_2$  is a direct bond or  $C_1-C_4$ alkylene,

$R_{22}$  is as defined for  $R_{10}$ ,

$R_{23}$ ,  $R_{24}$ ,  $R_{27}$  and  $R_{28}$  independently of one another are hydrogen,  $C_1-C_{30}$ alkyl,  $C_5-C_{12}$ cycloalkyl or phenyl,

$R_{25}$  is hydrogen,  $C_1-C_{30}$ alkyl,  $C_5-C_{12}$ cycloalkyl, phenyl,  $C_7-C_9$ phenylalkyl or a group of the formula IV-1 and

$n_5$  is a number from 1 to 50.

26. A stabilizer mixture according to claim 1 substantially as hereinbefore described with reference to any one of the foregoing Examples.



Application N : GB 9607380.4 Examiner: Miss Maureen M. Kelman  
Claims searched: 1 to 6,9 to 16 and 26, for a Date of search: 18 July 1996  
mixture of I-a) with any of  
II-a) to II-m)

**Patents Act 1977**  
**Search Report under Section 17**

**Databases searched:**

UK Patent Office collections, including GB, EP, WO & US patent specifications, in:

UK Cl (Ed.O): C3K KCB KCZ

Int Cl (Ed.6): C08K 5/00, 5/3435, 5/3492, 5/54

Other:

**Documents considered to be relevant:**

Category	Identity of document and relevant passage	Relevant to claims
X	GB 2267499 A SANDOZ see page 7, lines 13 to 14, page 15, lines 3 to 7, and page 16	1 to 6,9 to 16,26
X	WO 94/22946 A2 D&S PLASTICS see Table VIII on page 17	1 to 6,9 to 16,26
A	WO 92/12201 A1 SANDOZ	
X	US 4957953 A ADEKA see Examples 1-18 and 2-12	1,2,4,5,9, 11 to 16,26

X	Document indicating lack of novelty or inventive step	A	Document indicating technological background and/or state of the art.
Y	Document indicating lack of inventive step if combined with one or more other documents of same category.	P	Document published on or after the declared priority date but before the filing date of this invention.
&	Member of the same patent family	E	Patent document published on or after, but with priority date earlier than, the filing date of this application.